

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Machine Id

015-0064 (S/N 236017)

Swing Drive Fluid SCHAEFFER 267 80W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Swing motor sample)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0868300	WC0815102	WC0814964
Sample Date		Client Info		10 Jun 2024	02 Oct 2023	18 Jul 2023
Machine Age	hrs	Client Info		10189	9217	8857
Oil Age	hrs	Client Info		2196	0	0
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	1	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>400	11	9	9
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>10	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	3	2	0
Lead	ppm	ASTM D5185m	>50	<1	<1	0
Copper	ppm	ASTM D5185m	>200	<1	0	0
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		100	103	127
Barium	ppm	ASTM D5185m		2	0	0
Volybdenum	ppm	ASTM D5185m		396	372	407
Vanganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		1	0	0
Calcium	ppm	ASTM D5185m		37	30	43
Phosphorus	ppm	ASTM D5185m		1093	1051	1226
Zinc	ppm	ASTM D5185m		19	13	2
Sulfur	ppm	ASTM D5185m		21022	19481	26078
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		6	4	4
Sodium	ppm	ASTM D5185m		1	2	3
Potassium	ppm	ASTM D5185m	>20	2	3	2
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
0:14	scalar	*Visual	NONE	NONE	NONE	NONE
Silt					LIQUIT	NONE
	scalar	*Visual	NONE	NONE	LIGHT	
Debris	scalar scalar	*Visual *Visual	NONE	NONE NONE	NONE	NONE
Debris Sand/Dirt						
Debris Sand/Dirt Appearance	scalar	*Visual	NONE	NONE	NONE	NONE
Silt Debris Sand/Dirt Appearance Odor Emulsified Water	scalar scalar	*Visual *Visual	NONE NORML	NONE NORML	NONE NORML	NONE NORML



OIL ANALYSIS REPORT



	FLUID PROPER	TIES	nethod	limit/base	current	history1	history2
	Visc @ 40°C	cSt AS	STM D445	220	108	110	107
C: 4	SAMPLE IMAGE	IS I	method	limit/base	current	history1	history2
	Color				no image	no image	no image
Jul18/23 Jun10/24	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys						
	25 20 <u>East</u> 15 10			_			
	N 0	0ct4/21	Jul18/23	Jun10/24			
	Non-ferrous Meta	als					
	9 - copper 8 - lead 7 - 6 - 6 - 6 - 7 - 7 - 7 - 7 - 7 - 7 -						
	Nov11/19	0ct4/21	Jul18/23	Jun 10/24			
	Viscosity @ 40°C						
	220 - 200 - 						
	140 120 - Abnormal						
	100	0ct4/210ct4/22	Jul18/23	Jun10/24			
Laboratory Sample No. Lab Number Unique Number Test Package	: 11083384	Received Tested Diagnos	d : 14 : 18 ed : 18	Jun 2024 Jun 2024 Jun 2024 - Se	an Felton	CHAT Contact: DA	NSTRUCTION LHEAD DRIVE FANOOGA, TN US 37415 NIEL LISELLA

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Submitted By: TECH TECHNICIAN Page 2 of 2

daniel.lisella@shimmick.com

Т:

F: