

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

015-0064 (S/N 236017)

Rear Left Final Drive Fluid SCHAEFFER 267 80W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Rear left final drive sample $\ensuremath{)}$

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		WC0868279	WC0815097	WC0814955			
Sample Date		Client Info		10 Jun 2024	02 Oct 2023	18 Jul 2023			
Machine Age	hrs	Client Info		10189	9217	8857			
Oil Age	hrs	Client Info		1121	0	0			
Oil Changed		Client Info		N/A	Not Changd	Not Changd			
Sample Status				NORMAL	NORMAL	NORMAL			
CONTAMINATION	١	method	limit/base	current	history1	history2			
Water		WC Method	>0.2	NEG	NEG	NEG			
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>500	41	44	41			
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1			
Nickel	ppm	ASTM D5185m	>10	<1	<1	<1			
Titanium	ppm	ASTM D5185m		0	<1	0			
Silver	ppm	ASTM D5185m		0	0	0			
Aluminum	ppm	ASTM D5185m	>25	4	0	2			
Lead	ppm	ASTM D5185m	>25	8	7	7			
Copper	ppm	ASTM D5185m	>50	29	28	25			
Tin	ppm	ASTM D5185m	>10	2	2	2			
Vanadium	ppm	ASTM D5185m		0	0	0			
Cadmium	ppm	ASTM D5185m		0	0	0			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		34	24	34			
Barium	ppm	ASTM D5185m		2	2	0			
Molybdenum	ppm	ASTM D5185m		355	336	347			
Manganese	ppm	ASTM D5185m		1	1	2			
Magnesium	ppm	ASTM D5185m		6	5	<1			
Calcium	ppm	ASTM D5185m		11	16	11			
Phosphorus	ppm	ASTM D5185m		1092	1117	1193			
Zinc	ppm	ASTM D5185m		26	22	7			
Sulfur	ppm	ASTM D5185m		23161	22260	27287			
CONTAMINANTS		method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>75	8	10	9			
Sodium	ppm	ASTM D5185m		1	<1	3			
Potassium	ppm	ASTM D5185m	>20	3	2	4			
VISUAL		method	limit/base	current	history1	history2			
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE			
Silt	scalar	*Visual	NONE	NONE	NONE	NONE			
Debris	scalar	*Visual	NONE	NONE	NONE	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE			
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML			
Odor	scalar	*Visual	NORML	NORML	NORML	NORML			
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG			
Free Water	scalar	*Visual		NEG	NEG	NEG			
04:48:02) Rev: 1				Submitted By: TECH TECHNICIAN					



OIL ANALYSIS REPORT



	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	220	112	113.5	112
/23	SAMPLE IMAGE	S	method	limit/base	current	history1	history2
	Color				no image	no image	no image
Jul18/23 0ct2/23 Jun10/24	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys	May4/22 + 0et24/22 + 0	Mar17/23 Mar	Junt0/24			
Laboratory	: WearCheck USA - 5		on Ave., Cary				

: 14 Jun 2024



 Lab Number
 : 06210622
 Tested
 : 17 Jun 2024

 Unique Number
 : 11083486
 Diagnosed
 : 17 Jun 2024 - Angela Borella

 Certificate L2367
 Test Package
 : CONST

 To discuss this sample report, contact Customer Service at 1-800-237-1369.

 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Sample No. : WC0868279

5535 TRAILHEAD DRIVE CHATTANOOGA, TN

US 37415 Contact: DANIEL LISELLA daniel.lisella@shimmick.com T: :2012) F:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received

Submitted By: TECH TECHNICIAN Page 2 of 2