


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

BC-12 (S/N TDSL283L0206HH)

Refrigeration Compressor

CAMCO 717 HT (150 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0936189	WC0914844	WC0844684
Sample Date		Client Info		09 Jun 2024	07 Mar 2024	15 Sep 2023
Machine Age	hrs	Client Info		176997	0	172854
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	<1	0	3
Chromium	ppm	ASTM D5185m	>2	0	<1	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	2	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m	>8	<1	0	<1
Tin	ppm	ASTM D5185m	>4	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m		0	<1	<1
Calcium	ppm	ASTM D5185m		0	3	2
Phosphorus	ppm	ASTM D5185m		<1	0	2
Zinc	ppm	ASTM D5185m		1	0	6
Sulfur	ppm	ASTM D5185m		30	0	240
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	0	1
Sodium	ppm	ASTM D5185m		2	0	0
Potassium	ppm	ASTM D5185m	>20	0	1	<1
Water	%	ASTM D6304	>0.01	0.002	0.001	0.001
ppm Water	ppm	ASTM D6304	>100	19	10	12.7
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.014

Acid Number (AN)


mg KOH/g ASTM D974 0.007


0.015


0.016



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG

LLOID PHOPE	N I IEO	method			riistory i	HISTORY
Visc @ 40°C	cSt	ASTM D445	69	67.9	71.3	110


SAMPLE IMAGES	method		history2


Color







GRAPHS













Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0936189 Lab Number : 06211739 Unique Number : 11084603

Received **Tested** Diagnosed

: 17 Jun 2024 : 18 Jun 2024 : 18 Jun 2024 - Don Baldridge

PARK RAPIDS, MN

US 56470 Contact: MICHAEL GRUIS michael.gruis@lambweston.com

T: (218)732-2188 F: (218)732-2175

LAMB WESTON/RDO

Test Package : IND 2 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PO BOX 552