


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id FSP137682

Component

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


		Oct2019	Jun2021	Jul2022 Mar2023 Jan2024	Jun2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0875930	WC0903240	WC0875867
Sample Date		Client Info		07 Jun 2024	28 Mar 2024	19 Jan 2024
Machine Age	mls	Client Info		206243	202938	19772
Oil Age	mls	Client Info		0	0	10000
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	13	13	24
Chromium	ppm	ASTM D5185m	>20	<1	<1	1
Nickel	ppm	ASTM D5185m	>4	<1	<1	<1
Titanium	ppm	ASTM D5185m		1	6	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	3	4
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	<1
Cadmium	ppm	ASTM D5185m		<1	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	315	198	178
Barium	ppm	ASTM D5185m	10	<1	0	0
Molybdenum	ppm	ASTM D5185m	100	79	57	89
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	450	417	582	456
Calcium	ppm	ASTM D5185m	3000	1303	1523	1323
Phosphorus	ppm	ASTM D5185m	1150	1014	913	967
Zinc	ppm	ASTM D5185m	1350	1140	1117	1257
Sulfur	ppm	ASTM D5185m	4250	2917	3947	3094
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	4	6
Sodium	ppm	ASTM D5185m	>158	2	2	4
Potassium	ppm	ASTM D5185m	>20	3	3	3
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.6
Nitration	Abs/cm	*ASTM D7624	>20	7.8	9.3	9.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.9	21.8	24.4
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.0	18.3	20.2
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.1	6.7	5.7



OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method				history2	
Visc @ 100°C	cSt	ASTM D445	14.4	13.1	13.0	13.2	

GRAPHS













Certificate 12367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0875930 Lab Number : 06212956 Unique Number : 11085820

Test Package : FLEET

Received : 17 Jun 2024 **Tested** : 19 Jun 2024

Diagnosed : 19 Jun 2024 - Wes Davis

FRESHPOINT 8801 EXCHANGE DRVIE ORLANDO, FL US 32809

Contact: CRAIG EVANS evans_craig@sbcglobal.net T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: CRAIG EVANS - FREORL

F: