




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
L-440
 Component
Diesel Engine
 Fluid
PHILLIPS 66 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			WC0703799	WC0878710	WC0703812
Sample Date	Client Info			14 Jun 2024	18 Mar 2024	22 Jan 2024
Machine Age	hrs	Client Info		2279	1849	1582
Oil Age	hrs	Client Info		430	267	259
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<1.0	<1.0	<1.0
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	9	2	4
Chromium	ppm	ASTM D5185m	>20	0	0	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	1	4
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	2	0	<1
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		48	73	72
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		97	95	93
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		29	47	22
Calcium	ppm	ASTM D5185m		2685	2374	2557
Phosphorus	ppm	ASTM D5185m		1158	1110	1116
Zinc	ppm	ASTM D5185m		1404	1299	1277
Sulfur	ppm	ASTM D5185m		4935	4760	4155

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4	3	4
Sodium	ppm	ASTM D5185m		2	<1	0
Potassium	ppm	ASTM D5185m	>20	<1	0	<1


INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.3	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.5	8.3	8.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.7	17.3	17.9

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.4	13.9	13.8
Base Number (BN)	mg KOH/g	ASTM D2896		6.1	6.9	6.6




OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number







Viscosity @ 100°C



PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.9	13.9	13.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : WC0703799 Received : 18 Jun 2024
 Lab Number : 06213247 Tested : 19 Jun 2024
 Unique Number : 11086111 Diagnosed : 19 Jun 2024 - Wes Davis
 Test Package : CONST (Additional Tests: TBN)

DUKE LAZZARA
 4201 FAYETTEVILLE RD
 RALEIGH, NC
 US 27603
 Contact: BRANDON BYRUM
 b.byrum@dukelazzara.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: