OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
[AFTER FILTRATION]
Machine Id
432052.01
Component
Hydraulic System
Fluid
AW HYDRAULIC OIL ISO 46 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**KL0014375**	KL0014374	---
Sample Date		Client Info		**05 Jun 2024**	04 Jun 2024	---
Machine Age	hrs	Client Info		**0**	0	---
Oil Age	hrs	Client Info		**0**	0	---
Oil Changed		Client Info		**N/A**	N/A	---
Sample Status				**NORMAL**	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.05	**NEG**	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	**7**	7	---
Chromium	ppm	ASTM D5185m	>20	**2**	1	---
Nickel	ppm	ASTM D5185m	>20	**<1**	<1	---
Titanium	ppm	ASTM D5185m		**<1**	<1	---
Silver	ppm	ASTM D5185m		**<1**	<1	---
Aluminum	ppm	ASTM D5185m	>20	**2**	2	---
Lead	ppm	ASTM D5185m	>20	**<1**	<1	---
Copper	ppm	ASTM D5185m	>20	**6**	6	---
Tin	ppm	ASTM D5185m	>20	**<1**	<1	---
Vanadium	ppm	ASTM D5185m		**0**	0	---
Cadmium	ppm	ASTM D5185m		**<1**	<1	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	**0**	0	---
Barium	ppm	ASTM D5185m	5	**<1**	<1	---
Molybdenum	ppm	ASTM D5185m	5	**<1**	<1	---
Manganese	ppm	ASTM D5185m		**<1**	<1	---
Magnesium	ppm	ASTM D5185m	25	**12**	20	---
Calcium	ppm	ASTM D5185m	200	**13**	12	---
Phosphorus	ppm	ASTM D5185m	300	**219**	226	---
Zinc	ppm	ASTM D5185m	370	**244**	264	---
Sulfur	ppm	ASTM D5185m	2500	**3429**	3045	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	**2**	3	---
Sodium	ppm	ASTM D5185m		**0**	0	---
Potassium	ppm	ASTM D5185m	>20	**1**	1	---

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		**199**	608	---
Particles >6µm		ASTM D7647	>1300	**64**	155	---
Particles >14µm		ASTM D7647	>160	**7**	13	---
Particles >21µm		ASTM D7647	>40	**1**	4	---
Particles >38µm		ASTM D7647	>10	**0**	0	---
Particles >71µm		ASTM D7647	>3	**0**	0	---
Oil Cleanliness		ISO 4406 (c)	>17/14	**13/10**	14/11	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	**0.18**	0.22	---

OIL ANALYSIS REPORT

Particle Trend



Acid Number



Viscosity @ 40°C



Particle Trend



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	---
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	---
Silt	scalar	*Visual	NONE	**NONE**	NONE	---
Debris	scalar	*Visual	NONE	**NONE**	NONE	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	---
Appearance	scalar	*Visual	NORML	**NORML**	NORML	---
Odor	scalar	*Visual	NORML	**NORML**	NORML	---
Emulsified Water	scalar	*Visual	>0.05	**NEG**	NEG	---
Free Water	scalar	*Visual		**NEG**	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	**45.6**	45.7	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					*no image*
Bottom					*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number

Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KL0014375
Lab Number : 06213431
Unique Number : 11086295
Test Package : MOB 2

Received : 18 Jun 2024
Tested : 19 Jun 2024
Diagnosed : 19 Jun 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PV FLUID PRODUCTS
11901 CUTTEN RD
HOUSTON, TX
US 77066
Contact: PAT HARRAH
PAT.HARRAH@PVFLUID.COM
T: (281)620-2085
F: