




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Machine Id  
**PRINCETON 1356**

Component  
**Diesel Engine**

Fluid  
 **DIESEL ENGINE OIL SAE 5W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

Metal levels are typical for a new component breaking in.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| SAMPLE INFORMATION |             | method      | limit/base | current            | history1    | history2 |
|--------------------|-------------|-------------|------------|--------------------|-------------|----------|
| Sample Number      | Client Info |             |            | <b>WC0917105</b>   | WC0893814   | ---      |
| Sample Date        | Client Info |             |            | <b>06 May 2024</b> | 01 Feb 2024 | ---      |
| Machine Age        | hrs         | Client Info |            | <b>652</b>         | 605         | ---      |
| Oil Age            | hrs         | Client Info |            | <b>0</b>           | 0           | ---      |
| Oil Changed        | Client Info |             |            | <b>Changed</b>     | Changed     | ---      |
| Sample Status      |             |             |            | <b>NORMAL</b>      | ATTENTION   | ---      |

| CONTAMINATION |           | method | limit/base | current        | history1 | history2 |
|---------------|-----------|--------|------------|----------------|----------|----------|
| Fuel          | WC Method | >5     |            | <b>&lt;1.0</b> | <1.0     | ---      |
| Water         | WC Method | >0.2   |            | <b>NEG</b>     | NEG      | ---      |
| Glycol        | WC Method |        |            | <b>NEG</b>     | NEG      | ---      |

| WEAR METALS |     | method      | limit/base | current      | history1 | history2 |
|-------------|-----|-------------|------------|--------------|----------|----------|
| Iron        | ppm | ASTM D5185m | >100       | <b>4</b>     | <1       | ---      |
| Chromium    | ppm | ASTM D5185m | >20        | <b>&lt;1</b> | <1       | ---      |
| Nickel      | ppm | ASTM D5185m | >4         | <b>0</b>     | 0        | ---      |
| Titanium    | ppm | ASTM D5185m |            | <b>0</b>     | 0        | ---      |
| Silver      | ppm | ASTM D5185m | >3         | <b>0</b>     | 0        | ---      |
| Aluminum    | ppm | ASTM D5185m | >20        | <b>2</b>     | 2        | ---      |
| Lead        | ppm | ASTM D5185m | >40        | <b>0</b>     | 0        | ---      |
| Copper      | ppm | ASTM D5185m | >330       | <b>&lt;1</b> | 0        | ---      |
| Tin         | ppm | ASTM D5185m | >15        | <b>0</b>     | 0        | ---      |
| Vanadium    | ppm | ASTM D5185m |            | <b>0</b>     | 0        | ---      |
| Cadmium     | ppm | ASTM D5185m |            | <b>0</b>     | 0        | ---      |

| ADDITIVES  |     | method      | limit/base | current     | history1 | history2 |
|------------|-----|-------------|------------|-------------|----------|----------|
| Boron      | ppm | ASTM D5185m | 250        | <b>90</b>   | 98       | ---      |
| Barium     | ppm | ASTM D5185m | 10         | <b>0</b>    | 0        | ---      |
| Molybdenum | ppm | ASTM D5185m | 100        | <b>76</b>   | 65       | ---      |
| Manganese  | ppm | ASTM D5185m |            | <b>0</b>    | <1       | ---      |
| Magnesium  | ppm | ASTM D5185m | 450        | <b>941</b>  | 973      | ---      |
| Calcium    | ppm | ASTM D5185m | 3000       | <b>1252</b> | 1255     | ---      |
| Phosphorus | ppm | ASTM D5185m | 1150       | <b>857</b>  | 881      | ---      |
| Zinc       | ppm | ASTM D5185m | 1350       | <b>970</b>  | 1002     | ---      |
| Sulfur     | ppm | ASTM D5185m | 4250       | <b>2230</b> | 2342     | ---      |

| CONTAMINANTS |     | method      | limit/base | current      | history1 | history2 |
|--------------|-----|-------------|------------|--------------|----------|----------|
| Silicon      | ppm | ASTM D5185m | >25        | <b>4</b>     | 5        | ---      |
| Sodium       | ppm | ASTM D5185m | >44        | <b>&lt;1</b> | <1       | ---      |
| Potassium    | ppm | ASTM D5185m | >20        | <b>2</b>     | 0        | ---      |


| INFRA-RED |          | method      | limit/base | current     | history1 | history2 |
|-----------|----------|-------------|------------|-------------|----------|----------|
| Soot %    | %        | *ASTM D7844 | >3         | <b>0</b>    | 0        | ---      |
| Nitration | Abs/cm   | *ASTM D7624 | >20        | <b>7.3</b>  | 6.8      | ---      |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30        | <b>12.4</b> | 12.6     | ---      |

| FLUID DEGRADATION |          | method      | limit/base | current     | history1 | history2 |
|-------------------|----------|-------------|------------|-------------|----------|----------|
| Oxidation         | Abs/.1mm | *ASTM D7414 | >25        | <b>8.6</b>  | 9.1      | ---      |
| Base Number (BN)  | mg KOH/g | ASTM D2896  | 8.5        | <b>10.3</b> | 10.2     | ---      |




# OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number




Viscosity @ 100°C



| VISUAL           | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal      | scalar | *Visual    | NONE    | NONE     | ---      |
| Yellow Metal     | scalar | *Visual    | NONE    | NONE     | ---      |
| Precipitate      | scalar | *Visual    | NONE    | NONE     | ---      |
| Silt             | scalar | *Visual    | NONE    | NONE     | ---      |
| Debris           | scalar | *Visual    | NONE    | NONE     | ---      |
| Sand/Dirt        | scalar | *Visual    | NONE    | NONE     | ---      |
| Appearance       | scalar | *Visual    | NORML   | NORML    | ---      |
| Odor             | scalar | *Visual    | NORML   | NORML    | ---      |
| Emulsified Water | scalar | *Visual    | >0.2    | NEG      | ---      |
| Free Water       | scalar | *Visual    |         | NEG      | ---      |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| Visc @ 100°C     | cSt    | ASTM D445  | 14.4    | 12.6     | 13.2     |

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0917105  
**Lab Number** : 06214215  
**Unique Number** : 11087079  
**Test Package** : MOB 1 ( Additional Tests: TBN )

**CONCRETE SERVICE CO - FAY BLOCK**  
 161 BUILDERS BLVD  
 FAYETTEVILLE, NC  
 US 28301

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact: BRYAN VANNIMAN  
 bryanvanniman@fayblock.com  
 T: (800)326-9198

F: