

## **OIL ANALYSIS REPORT**

Sample Number

mls

mls

Sample Date

Machine Age

Oil Changed

Sample Status

Oil Age

Water

Glycol

### Area [WO36040] **FREIGHTLINER TRK 2013**

**Diesel Engine** Fluid PETRO CANADA DURON SHP 15W40 (--- GAL)

#### Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor. ( Customer Sample Comment: FIRST OIL CHANGE)

### Wear

Metal levels are typical for a components first oil change.

#### Contamination

Fuel content negligible. Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components.

#### Fluid Condition

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.



WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>80	55		
Chromium	ppm	ASTM D5185m	>5	5		
Nickel	ppm	ASTM D5185m	>2	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>30	152		
Lead	ppm	ASTM D5185m	>30	<1		
Copper	ppm	ASTM D5185m	>150	174		
Tin	ppm	ASTM D5185m	>5	2		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		


ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	24		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	60	37		
Manganese	ppm	ASTM D5185m	0	7		
Magnesium	ppm	ASTM D5185m	1010	475		
Calcium	ppm	ASTM D5185m	1070	1710		
Phosphorus	ppm	ASTM D5185m	1150	682		
Zinc	ppm	ASTM D5185m	1270	822		
Sulfur	ppm	ASTM D5185m	2060	2103		


CONTAMINA	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	8		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	352		
Fuel	%	ASTM D3524	>5	0.0		

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.6		
Nitration	Abs/cm	*ASTM D7624	>20	10.0		
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.9		
FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	23.1		
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.4		



# **OIL ANALYSIS REPORT**





To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (910)862-4344

Certificate 12367

Submitted By: Cassie Priest

cassiep@campbelloilcompany.com

T: