

OIL ANALYSIS REPORT

Area ULTRA COOLANT Machine Id CBV478015 - MUSCATINE COMM SCHOOL

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06214838	UCH05875624	
Sample Date		Client Info		07 Jun 2024	01 Jun 2023	
Machine Age	hrs	Client Info		4850	3869	
Oil Age	hrs	Client Info		2500	512	
Oil Changed		Client Info		Not Changd	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	<1	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	<1	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	<1	2	
Tin	ppm	ASTM D5185m	>15	<1	<1	
Vanadium	ppm	ASTM D5185m		0	<1	
Cadmium	ppm	ASTM D5185m		0	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<1	0	
Barium	ppm	ASTM D5185m	500	242	370	
Molybdenum	ppm	ASTM D5185m	0	0	<1	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m	0	0	1	
Calcium	ppm	ASTM D5185m	0	5	5	
Phosphorus	ppm	ASTM D5185m	20	4	6	
Zinc	ppm	ASTM D5185m	0	22	32	
Sulfur	ppm	ASTM D5185m	200	380	423	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	2	
Sodium	ppm	ASTM D5185m		65	42	
Potassium	ppm	ASTM D5185m	>20	4	4	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.15	0.08	


Sample Rating Trend



45 Severe 40 Jun1/23

OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base	e current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Jun7/24 •	Appearance	scalar	*Visual	NORML	NORML	NORML	
n L	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERTI	IFS	method	limit/base	e current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	49.4	51.2	50.8	
	SAMPLE IMAGES		method	limit/base		history1	history2
	SAMPLE IMAGES		method	iiiiii/base			THSTOLY2
- + + 52/	Color						no image
	Bottom					$\left(\begin{array}{c} \\ \end{array}\right)$	no image
	GRAPHS						
	Ferrous Alloys						
	10 iron						
	o assessesses chromium						
	E 6						
	2						
	0						
	Jun1/23			Jun7/24			
	η			ηr			
	Non-ferrous Metals	5					
	10 copper						
	o - sesses lead						
	2						
	0			4			
	Jun1/23			Jun7/24			
	⊃ Viscosity @ 40°C			7			
	70 Severe			-2	Acid Number		
	65 Abnormal			B/HO) 2	.00		
	다 60 + 0 - 0 - 0 - 55 - 평 50 + Bboomal			.2 .2 .1 .0 .0 .0 .0 .0 .0 .0 .0 .0 .0 .0 .0 .0	50 Abnormal		
	ස් දි 50 - දිදිසල mal			ng 1.			
	45 Severe			N Pg 0.	50		
	404			U.	.00		
	Jun 1/23			Jun7/24	Jun1/23		
Laboratory Sample No. Lab Number Unique Number Test Package iscuss this sample report	: 11087702	A-L-L EQUIPMENT IN 204 38TH 5 MOLINE, US 612 Contact: KEVIN DESPO kevind@a-I-lequipment.cc T: (815)877-70					

Report Id: UCALLMOL [WUSCAR] 06214838 (Generated: 06/21/2024 16:15:15) Rev: 1

Contact/Location: KEVIN DESPOT - UCALLMOL