<u>Sullivan</u> Palatek.

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area **RAGE U46** Machine Id **SULLAIR 003-112023 - MALNOVE** Component

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCS06214849	UCS06135103	
Sample Date		Client Info		13 Jun 2024	31 Mar 2024	
Machine Age	hrs	Client Info		1934	11383	
Oil Age	hrs	Client Info		796	0	
Oil Changed		Client Info		Not Changd	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	
Chromium	ppm	ASTM D5185m	>10	0	<1	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	<1	0	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	0	0	
Tin	ppm	ASTM D5185m	>15	<1	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		17	5	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m		0	<1	
Calcium	ppm	ASTM D5185m		0	<1	
Phosphorus	ppm	ASTM D5185m		157	11	
Zinc	ppm	ASTM D5185m		0	0	
Sulfur	ppm	ASTM D5185m		598	45	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1	2	
Sodium	ppm	ASTM D5185m		1	4	
Potassium	ppm	ASTM D5185m	>20	2	1	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.48	0.55	



OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base		history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
3/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
Jun13/24	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	innibase	46.5	49.3	
	SAMPLE IMAGES		method	limit/base	current	history1	history2
	SAMPLE IMAGES	D	methou	IIIIII/Dase	current	TIISTOTYT	TIIStOLYZ
Jun1324 +	Color						no image
	Bottom						no image
	Non-ferrous Metal	5		Jun13/24	Acid Number		
	Viscosity @ 40°C			(^{0.60}			
	55 Abnormal			0.60 HO 0.48 E 0.36			
	55 50 \$145 \$3			(0.60 例 0.48 例 0.36 單 0.24			
	55 Abnormal			(5,0,60 (5,0,0,48 (5,0,0,48) (5,0,0,48) (5,0,0,48) (5,0,0,48) (5,0,0,48) (5,0,0,48) (5,0,0,48) (5,0,0,0,48) (5,0,0,0,48) (5,0,0,0,48) (5,0,0,0,48) (5,0,0,0,48) (5,0,0,48)(5,0,0,48) (5,0,0,48)(5,0,0,48) (5,0,0,48)(5,0,0,48)(5,0,			
	55 50 \$145 \$3			(B)HO) 0.48 (B)HO) 0.48 (B)HO) 0.48 (B)HO) 0.24 (B)HO (C)H	Mar31/24		
	55 50 \$145 \$3			(b) 0.60 (b) 0.48 (b) 0.36 (c) 0.24 (c) 0.24 (c) 0.24			

Contact/Location: CHASE SVOBODA - UCRASWAT