

OIL ANALYSIS REPORT

Sample Rating Trend

DIRT



Machine Id MTNM01BE Component

Component Biogas Engine

SHELL MYSELLA S5 N 40 (160 GAL)

SAMPLE INFORM	MATION	method	limit/base	current	history1	history
Sample Number		Client Info		WC0775201	WC0775202	WC077519
Sample Date		Client Info		17 Jun 2024	13 Jun 2024	28 May 202
Machine Age	hrs	Client Info		43228	43136	43106
Oil Age	hrs	Client Info		443	351	391
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method		NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history
PQ		ASTM D8184		18	17	
Iron	ppm	ASTM D5185m	>14	5	4	4
Chromium	ppm	ASTM D5185m	>3	0	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>5	3	3	3
Lead	ppm	ASTM D5185m	>8	0	0	0
Copper	ppm	ASTM D5185m	>5	2	1	1
Tin	ppm	ASTM D5185m	>3	1	0	4
Vanadium	ppm	ASTM D5185m		<1	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history
Boron	ppm	ASTM D5185m		6	6	2
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		2	2	1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		25	22	17
Calcium	ppm	ASTM D5185m		1889	1743	1795
Phosphorus	ppm	ASTM D5185m	300	374	340	392
Zinc	ppm	ASTM D5185m		469	430	476
Sulfur	ppm	ASTM D5185m		3859	3579	4065
CONTAMINANTS	6	method	limit/base	current	history1	history
Silicon	ppm	ASTM D5185m	>180	1 85	130	173
Sodium	ppm	ASTM D5185m	>20	3	3	1
Potassium	ppm	ASTM D5185m	>20	<1	1	0
INFRA-RED		method	limit/base	current	history1	history
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>16	5.3	4.5	5.1
Sulfation	Abs/.1mm	*ASTM D7415		23.6	20.4	23.2

DIAGNOSIS

A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Elemental level of silicon (Si) above normal.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





OIL ANALYSIS REPORT


FT-IR (Direct Trend)











method

ASTM D445


limit/base

Base 0.0


13.5



Visc @ 100°C




cSt




Jul13/23

Jov17/23

Dec19/73





history1

13.6

current

13.8

history2

history2

15.7

1.90

3.28

NONE

NONE

NONE

NONE

NONE

NONE

NORML


NORML

historv2

NEG

NEG

13.7



Vov17/23

ler19/23

P0/249 lar4/74 10/74 Aav12/24

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 **EDL NA Recips-Morgantown** Sample No. : WC0775201 Received : 19 Jun 2024 Morgantown Powerstation, 950 Shiloh Lab Number Tested : 20 Jun 2024 : 06214923 Unique Number : 11087787 Diagnosed : 21 Jun 2024 - Sean Felton Test Package : MOB 2 (Additional Tests: PQ) Contact: ARON GUNN Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. aron.gunn@edlenergy.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

/ar4/24

40174

Mav12/24

Report Id: EDLMOR [WUSCAR] 06214923 (Generated: 06/21/2024 13:56:27) Rev: 1

Submitted By: LANDON WEBER

Page 2 of 2

Morgantown, PA

US 19543

T:

F: