

OIL ANALYSIS REPORT



Machine Id

Fluid

LEROI OXY0079 Component Compressor

CIMARRON HB-150 (--- GAL)

DIAGNOSIS

A Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

A Wear

The iron level is abnormal. All other component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		TO90004540		
Sample Date		Client Info		10 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				ABNORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	6 1		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	7.0	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
			>25	۰ <1		
Aluminum	ppm	ASTM D5185m	>25 >25	<1 <1		
Lead	ppm	ASTM D5185m				
Copper	ppm		>50	0		
Tin	ppm	ASTM D5185m	>15	1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	0	2		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	0	14		
Zinc	ppm	ASTM D5185m	0	3		
Sulfur	ppm	ASTM D5185m	0	1577		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	2		
Sodium	ppm	ASTM D5185m		4		
Potassium	ppm	ASTM D5185m	>20	6		
Water	%	ASTM D6304	>2.26	0.106		
www.Water	ppm	ASTM D6304	>22600	1060		
ppm water	1+ 1+ · · · ·	/1011W D0004	>LL000	1000		
FLUID CLEANLIN		method	limit/base	current	history1	history2
FLUID CLEANLIN					history1	history2
FLUID CLEANLIN Particles >4µm		method	limit/base	current		
FLUID CLEANLIN Particles >4μm Particles >6μm		method ASTM D7647	limit/base >10000	current		
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm		method ASTM D7647 ASTM D7647	limit/base >10000 >2500 >320	current ▲ 53294 ▲ 13843		
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm		method ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >320	current ▲ 53294 ▲ 13843 ▲ 589		
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >320 >80	current ▲ 53294 ▲ 13843 ▲ 589 ▲ 124		
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm Particles >71μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >320 >80 >20	current ▲ 53294 ▲ 13843 ▲ 589 ▲ 124 8		
Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm Oil Cleanliness	IESS	method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ISO 4406 (c)	limit/base >10000 >2500 >320 >80 >20 >20 >4 >20/18/15	current ↓ 53294 ↓ 13843 ↓ 589 ↓ 124 & 0 ↓ 23/21/16	 	
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm Particles >71μm	IESS	method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >10000 >2500 >320 >80 >20 >4	current ▲ 53294 ▲ 13843 ▲ 589 ▲ 124 8 0	 	

Contact/Location: CARLOS LEAL - CIMCAR Page 1 of 2



OIL ANALYSIS REPORT



	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Jun 10/24	Appearance	scalar	*Visual	NORML	NORML		
nun	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>2.26	NEG		
1	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	FIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	151	132		
	Visc @ 100°C	cSt	ASTM D445	28	23.9		
	Viscosity Index (VI)	Scale	ASTM D2270	224	213		
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Jun 10/24							
'nŗ	Color					no image	no image
	Bottom					no image	no image
	GRAPHS	-					
	🔺 Ferrous Alloys				A Particle Count		
Jun 10/24				491,52	²⁰ T		T ²⁶
- -	60 - chromium			122,8	30 Severe		-24
	E 40 - nickel			30,71			-22
	20				Abnormal		
	2 ⁴		******	7,61	30		-20
	Jun10/24			Jun 10/24 1'6'1 ml	20-		-18
				- Ge			+20 +18 +16 +14 +12
	Non-ferrous Metal	IS		of partic	50-		-16
	8. copper			5 12 12	20 -		-14
				in in	30 -		-12
A CL A L	2				8-		10
-	0						
	10/24			Jun 10/24	2-		
	Junl			ղոր	0 4µ 6µ	14µ 21µ	38µ 71µ
	Viscosity @ 40°C				Acid Number	17/2 21/2	30µ 71µ
	¹⁷⁰ Abnormal			(B/HC	¹⁵ T		
	160			20.1	10-		
	() 100 Base () 150 Base			per (
	140 - Abnormal			1.0 Gid Number (mg KOH/g) 1.0 Acid Number (mg KOH/g)	15 +		
	130						
Vert	Jun 10/2			Jun 10/24	Jun 10/24		
Laboratory Sample No.	: WearCheck USA - 50	1 Madisc Rece				RON ENERGY 4425 GRAN	
Lab Number	r : <mark>06216319</mark> r :11089183	Teste		l Jun 2024 Jun 2024 - Do	n Baldridae	C	ARLSBAD, N M 88220-892

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: CIMCAR [WUSCAR] 06216319 (Generated: 06/24/2024 15:47:47) Rev: 1

Contact/Location: CARLOS LEAL - CIMCAR

F: