

## **OIL ANALYSIS REPORT**

### Area Molding PRESS 08 (S/N 61002721)

Hydraulic System SHELL TELLUS S3 M 46 (45 GAL)

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.




SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ST46702	ST44364	ST40917
Sample Date		Client Info		15 May 2024	01 Dec 2022	09 Dec 2020
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>40	2	<1	2
Chromium	ppm	ASTM D5185m		<1	0	<1
Nickel	ppm	ASTM D5185m	>20	<1	0	0
Titanium	ppm	ASTM D5185m	20	<1	0	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	<u>_</u> 4	3	<1	0
Lead	ppm	ASTM D5185m	>10	ر 1	0	0
Copper	ppm	ASTM D5185m		2	2	2
Tin	ppm	ASTM D5185m		2 <1	0	0
Antimony	ppm	ASTM D5185m	~ 1			0
Vanadium	ppm	ASTM D5185m		 <1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
	ppill					
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	3	1	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	0	0
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m	0	<1	0	0
Calcium	ppm	ASTM D5185m		28	28	30
Phosphorus	ppm	ASTM D5185m	106	76	76	80
Zinc	ppm	ASTM D5185m	0	18	30	22
Sulfur	ppm	ASTM D5185m		643	457	350
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	<1	0	<1
Sodium	ppm	ASTM D5185m		0	<1	0
Potassium	ppm	ASTM D5185m	>20	2	0	0
Water	%	ASTM D6304	>0.05	0.008	0.004	0.003
ppm Water	ppm	ASTM D6304	>500	87	43.4	29.9
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>640	129	▲ 16615	<b>2</b> 738
Particles >6µm		ASTM D7647	>80	28	<b>4</b> 702	<b>9</b> 78
Particles >14µm		ASTM D7647	>10	2	<b>1</b> 70	<b>1</b> 70
Particles >21µm		ASTM D7647	>3	0	<u> </u>	<b>1</b> 6
Particles >38µm		ASTM D7647	>3	0	1	0
Particles >71µm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>16/13/10	14/12/9	<b>1</b> /19/15	▲ 19/17/13
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.18	0.17	0.168


Contact/Location: Jonathan Vanbeekum - MENWAL


Report Id: MENWAL [WUSCAR] 06216838 (Generated: 06/25/2024 12:59:38) Rev: 1





# **OIL ANALYSIS REPORT**














Bottom



Test Package : IND 2 (Additional Tests: KF)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: MENWAL [WUSCAR] 06216838 (Generated: 06/25/2024 12:59:38) Rev: 1

Certificate 12367

Contact/Location: Jonathan Vanbeekum - MENWAL

jonathan.vanbeekum@menshen.com

T:

F: