

OIL ANALYSIS REPORT

Area PG-46 [293103] Machine Id PNEUTECH AK100017090 - CIMTECH PLASTIC Component

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UFD0002130		
Sample Date		Client Info		17 Jun 2024		
Machine Age	hrs	Client Info		8050		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		320		
Zinc	ppm	ASTM D5185m		140		
Sulfur	ppm	ASTM D5185m		108		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.22		



OIL ANALYSIS REPORT

VISUAL



	VIOONE		method	initia base	Guirchi	Thistory I	matoryz	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
1	Debris	scalar	*Visual	NONE	LIGHT			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
/24 -	Appearance	scalar	*Visual	NORML	NORML			
Jun 17/24	Odor	scalar	*Visual	NORML	NORML			
,	Emulsified Water	scalar	*Visual	>0.1	NEG			
				20.1				
1	Free Water	scalar	*Visual		NEG			
	FLUID PROPER	TIES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445		45.6			
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2	
+5/L1mL	Color					no image	no image	
	Bottom					no image	no image	
	Non-ferrous Meta	ls		Jun17/24				
	Viscosity @ 40°C			0.2 (0)(1)(1)(1)(1)(1)(1)(1)(1)(1)(1)(1)(1)(1)	Acid Number		17.7 T 1.11	
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report Denotes test methods that	: 11089831 : IND 2 , contact Customer Serv are outside of the ISO 1	Recei Teste Diagr vice at 1-8 7025 sco	ived : 21 ed : 24 nosed : 24 800-237-1368 ope of accred	Jun 2024 Jun 2024 Jun 2024 - Wes Davis 9.		FLUID-AIRE DYNAMIC: 225 SPRING LAKE DI ITASCA, I US 6014 Contact: ED DIENEI ed.diener@fluidairedynamics.cor T: (847)678-838 1106:2012) F		

Contact/Location: ED DIENER - UCFLUSCH