


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

FRICK TYSHOUP RC-2 (S/N XJF120S1725DD)

Refrigeration Compressor

USPI ALT-68 SC (15 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		±2011 Feb20	13 Jun2014 Nov2016	Jun2018 Jan2020 Jun2021 A	hpr2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0013128	USP0007799	USP0003099
Sample Date		Client Info		20 Jun 2024	21 Feb 2024	02 Nov 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	0	0	0
Chromium	ppm	ASTM D5185m	>2	<1	0	0
Nickel	ppm	ASTM D5185m		<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>3	0	0	0
Lead	ppm	ASTM D5185m	>2	<1	0	0
Copper	ppm	ASTM D5185m	>8	<1	0	0
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		<1	0	0
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		0	0	0
Calcium	ppm	ASTM D5185m		0	<1	0
Phosphorus	ppm	ASTM D5185m		0	0	0
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m	50	0	0	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2	1	0
Sodium	ppm	ASTM D5185m		0	<1	0
Potassium	ppm	ASTM D5185m	>20	1	<1	0
Water	%	ASTM D6304	>0.01	0.001	0.002	0.004
ppm Water	ppm	ASTM D6304	>100	10	19	43.7
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	554	2184	2732
Particles >6µm		ASTM D7647	>2500	173	427	535
Particles >14µm		ASTM D7647	>320	13	14	24
Particles >21µm		ASTM D7647	>80	4	2	6
Particles >38μm		ASTM D7647	>20	0	0	0
Particles >71μm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	16/15/11	18/16/11	19/16/12
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974	0.005	0.014	0.015	0.014





OIL ANALYSIS REPORT




Par 35k T	ticle T	rena						
201		m						
25k -	14,	μm						
20k	111111		0.00					
- 1EL W								
15k - 1 2 10k - 4bno	ormal	111111			A	۸.		
25k - 25k - 20k -	ormal			۸,	1	W	-^^	
0k 15k - 11/950	ormal 3/13	A_F	Nov3/16	Jun3/18 🔨	Jan 28/20	Vun29/21 ₹	☆	










FLUID PROPER	THES	method			riistory i	History
Visc @ 40°C	cSt	ASTM D445	65.6	66.0	66.7	66.2

SAMPLE IMAG	ES

Color

Bottom









Certificate 12367

Laboratory Sample No.

: USP0013128 Lab Number : 06217344 Unique Number : 11090208 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 21 Jun 2024

Tested : 25 Jun 2024 Diagnosed : 25 Jun 2024 - Doug Bogart

TYSON -HOUSTON -USP - TYSHOUPOR

300 PORTWELL RD. HOUSTON, TX US 77029

Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

 st - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: