


OIL ANALYSIS REPORT



ARIZONA GROUPING MACK 7137

Diesel Engine

NAPA Motor Oil 15W40 (9 GAL)





NORMAL

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0935457	WC0935445	WC0899593
Sample Date		Client Info		11 Jun 2024	04 May 2024	09 Apr 2024
Machine Age	hrs	Client Info		12089	11959	11896
Oil Age	hrs	Client Info		94	1433	1370
Oil Changed		Client Info		Changed	Not Changd	Not Changd
Sample Status				NORMAL	ATTENTION	ATTENTION
CONTAMINATION	٧	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	0.8
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>120	4	13	8
Chromium	ppm	ASTM D5185m		0	<1	0
Nickel	ppm	ASTM D5185m	>5	<1	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m		2	3	2
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m		1	4	0
Tin	ppm		>15	- <1	<1	<1
Vanadium	ppm	ASTM D5185m	>10	0	<1	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES	1-1-	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		64	6	14
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		3	11	13
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		575	63	84
Calcium	ppm	ASTM D5185m		1569	2207	2173
Phosphorus	ppm	ASTM D5185m		795	899	920
Zinc	ppm	ASTM D5185m		900	1036	1085
Sulfur	ppm	ASTM D5185m		3711	3439	4213
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		6	9	6
Sodium	ppm	ASTM D5185m	725	2	3	3
Potassium	ppm	ASTM D5185m	>20	4	4	3
INFRA-RED	PP	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>4	0.1	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>4		6.9	6.8
Sulfation	Abs/.1mm	*ASTM D7624	>30	7.0 17.7	17.6	17.4
FLUID DEGRADATION method limit/base current history1 history2						
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.7	10.7	11.2
Base Number (BN)	mg KOH/g	ASTM D2896		7.5	6.6	6.8



OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPERTIES		method			history2	
Visc @ 100°C	cSt	ASTM D445	13.4	12.0	12.0	

GRAPHS













Certificate 12367

Laboratory

Sample No. Lab Number : 06217548

: WC0935457 Unique Number : 11090412 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 21 Jun 2024 **Tested** : 24 Jun 2024

Diagnosed

: 24 Jun 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LIBERTY DISPOSAL

6401 S EASTERN AVE OKLAHOMA CITY, OK US 73149

Contact: CATHY ROSA c.rosa@ldi89.com

T: F: