




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
SCHTRUCK
 Machine Id
6409 [SCHTRUCK]
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2	
Sample Number	Client Info	SBP0007705	SBP0006992	SBP0005996	
Sample Date	Client Info	21 Jun 2024	19 Mar 2024	21 Nov 2023	
Machine Age	mls	Client Info	297948	258829	217795
Oil Age	mls	Client Info	39119	41034	35303
Oil Changed	Client Info	Changed	Changed	Changed	
Sample Status		NORMAL	NORMAL	NORMAL	

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Water	WC Method >0.2	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >80	14	17	15
Chromium	ppm ASTM D5185m >5	1	2	1
Nickel	ppm ASTM D5185m >2	0	1	<1
Titanium	ppm ASTM D5185m	<1	1	0
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >30	3	5	3
Lead	ppm ASTM D5185m >30	0	<1	0
Copper	ppm ASTM D5185m >150	10	21	37
Tin	ppm ASTM D5185m >5	0	2	2
Vanadium	ppm ASTM D5185m	<1	<1	0
Cadmium	ppm ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 0	1	<1	0
Barium	ppm ASTM D5185m 0	0	<1	2
Molybdenum	ppm ASTM D5185m 60	63	66	62
Manganese	ppm ASTM D5185m 0	<1	<1	0
Magnesium	ppm ASTM D5185m 1010	1031	1018	922
Calcium	ppm ASTM D5185m 1070	1197	1155	1100
Phosphorus	ppm ASTM D5185m 1150	1011	1072	915
Zinc	ppm ASTM D5185m 1270	1352	1298	1206
Sulfur	ppm ASTM D5185m 2060	3041	2629	2962

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >20	4	6	4
Sodium	ppm ASTM D5185m	2	<1	0
Potassium	ppm ASTM D5185m >20	2	7	6

INFRA-RED

method	limit/base	current	history1	history2
Soot %	% *ASTM D7844 >3	0.5	0.6	0.5
Nitration	Abs/cm *ASTM D7624 >20	8.5	8.7	8.6
Sulfation	Abs/.1mm *ASTM D7415 >30	20.4	20.2	20.5


FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	16.8	17.1	17.7
Base Number (BN)	mg KOH/g ASTM D2896 9.8	6.8	6.6	6.7




OIL ANALYSIS REPORT


FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.8

GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : SBP0007705 **Received** : 24 Jun 2024
Lab Number : **06219149** **Tested** : 25 Jun 2024
Unique Number : 11097346 **Diagnosed** : 25 Jun 2024 - Wes Davis
Test Package : FLEET

SCHMIDT TRANSPORTATION - 605449
 108 E Bay Road
 Plattsmouth, NE
 US 68048
 Contact: NICK DOTY
 doty@liquidtrucking.com
 T: (402)949-9398
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)