

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

KAESER 7624691 - DW FINE PACK (S/N 1134)

Compressor

KAESER SIGMA (OEM) S-460 (15 GAL)

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment:

Top Up Amount: 1 GAL)

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				-		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0705608	WC0915276	WC0795219
Sample Date		Client Info		18 Jun 2024	17 Apr 2024	14 Mar 2023
Machine Age	hrs	Client Info		28417	28417	19049
Oil Age	hrs	Client Info		28417	3000	2333
Oil Changed		Client Info		Oil Added	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	<1	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	<1	0	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	10	3	4
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	9	61	37
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m	90	33	54	62
Calcium	ppm	ASTM D5185m	2	0	<1	2
Phosphorus	ppm	ASTM D5185m		3	8	6
Zinc	ppm	ASTM D5185m		5	0	4
Sulfur	ppm	ASTM D5185m		21595	20551	17491
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1	<1	<1
Sodium	ppm	ASTM D5185m		18	28	30
Potassium	ppm	ASTM D5185m	>20	4	7	10
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.39

Acid Number (AN)


mg KOH/g ASTM D8045 0.4

0.48


0.36



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	46.1	45.6	45.1
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color						© Prof. S







Report Id: PALFOU [WUSCAR] 06219807 (Generated: 06/28/2024 00:28:45) Rev: 1

Laboratory Sample No.

Lab Number : 06219807

: WC0705608 Unique Number : 11098004

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Jun 2024

Tested : 26 Jun 2024 Diagnosed : 27 Jun 2024 - Don Baldridge

ELEVATED INDUSTRIAL SOLUTIONS - EIS 302 HUGHES ST FOUNTAIN INN, SC

US 29644 Contact: DARRIN WARD

Test Package : IND 2 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Bottom

dward@elevatedindustrial.com T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: DARRIN WARD

F: (864)862-7653