

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area KAESER S-460 **KAESER 1258 - G.H. PRINTING**

Component Compressor

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UDI0000398	UCH05173853	
Sample Date		Client Info		20 Jun 2024	14 Jan 2021	
Machine Age	hrs	Client Info		97627	75640	
Oil Age	hrs	Client Info		5200	6000	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m	>3	<1	1	
Titanium	ppm	ASTM D5185m	>3	0	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	0	0	
Lead	ppm	ASTM D5185m	>10	0	0	
Copper	ppm	ASTM D5185m	>50	9	13	
Tin	ppm	ASTM D5185m	>10	0	0	
Antimony	ppm	ASTM D5185m			0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m	90	0	0	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		<1	0	
Magnesium	ppm	ASTM D5185m	90	0	4	
Calcium	ppm	ASTM D5185m	2	0	0	
Phosphorus	ppm	ASTM D5185m		6	0	
Zinc	ppm	ASTM D5185m		0	3	
Sulfur	ppm	ASTM D5185m		18456	15145	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1	2	
Sodium	ppm	ASTM D5185m		2	3	
Potassium	ppm	ASTM D5185m	>20	2	0	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.43	0.404	






OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	nistory i	nistory2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Jun 20/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
Juni	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	46	44.1	44.0	
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Jun20/24	Color						no image
	Bottom						no image
	Non-ferrous Metals	5		Jun20/24			
	,			Jun20/24			
	Viscosity @ 40°C			0.0	Acid Number		
	50 \$45 + \$			(0,10,10,10,10,10,10,10,10,10,10,10,10,10	Base		
	35						
	Jan 14,21			Jun20/24	Jan 14,21		
Laboratory Sample No. Lab Number Unique Number	: WearCheck USA - 50 ⁻ : UDI0000398 : 06219821 : 11098018	1 Madisor Receiv Testeo Diagn	ved : 25 d : 26	, NC 27513 5 Jun 2024 5 Jun 2024 Jun 2024 - V			TISS STREE RS GROVE, US 6051



Report Id: UCDELDOW [WUSCAR] 06219821 (Generated: 06/30/2024 14:45:47) Rev: 1

Contact/Location: MICHAEL FERRIS - UCDELDOW