

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

KAESER 7084127 - ULBRICH PRECISION FLATWIRE (S/N 1124)

Compressor

KAESER SIGMA (OEM) S-460 (20 GAL)

|--|

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0943038	WC0915269	WC0763781
Sample Date		Client Info		19 Jun 2024	16 Apr 2024	17 Jan 2023
Machine Age	hrs	Client Info		29715	28863	21113
Oil Age	hrs	Client Info		1500	700	3502
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL
CONTAMINATIO	V	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	<1	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>10	<1	<1	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm		>50	4	6	11
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	29	55	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m	90	44	47	16
Calcium	ppm	ASTM D5185m	2	0	3	0
Phosphorus	ppm	ASTM D5185m		0	0	2
Zinc	ppm	ASTM D5185m		2	0	6
Sulfur	ppm	ASTM D5185m		21195	21825	20565
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	0	<1
Sodium	ppm	ASTM D5185m		12	9	3
Potassium	ppm	ASTM D5185m	>20	4	6	0
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.44

Acid Number (AN)


mg KOH/g ASTM D8045 0.4

0.44


0.42



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	43.8	44.0	44.3
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color						3400







Certificate 12367

Laboratory Sample No.

Lab Number : 06219858

: WC0943038 Unique Number : 11098055 Test Package : IND 2

Bottom

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received : 25 Jun 2024 **Tested** : 26 Jun 2024 Diagnosed : 26 Jun 2024 - Sean Felton

0.00 PG

ELEVATED INDUSTRIAL SOLUTIONS - EIS 302 HUGHES ST FOUNTAIN INN, SC US 29644

Contact: DARRIN WARD dward@elevatedindustrial.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (864)862-7653

Report Id: PALFOU [WUSCAR] 06219858 (Generated: 06/28/2024 00:29:26) Rev: 1

Contact/Location: DARRIN WARD - PALFOU

T: