

OIL ANALYSIS REPORT

Sample Rating Trend

DIRT

Machine Id PETERBILT 772

Component Diesel Engine

Pluid PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

🔺 Wear

The copper level is abnormal. Valve wear is indicated. Elemental level of copper (Cu) probably due to leaching of copper from copper components (i.e. cooling core) by the oil additives.

Contamination

Elemental level of silicon (Si) above normal.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

AL)			Mar2024	May2024		
SAMPLE INFORM		method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0005976	SBP0005814	
Sample Date		Client Info		11 May 2024	03 Mar 2024	
Machine Age	mls	Client Info		571771	542079	
Dil Age	mls	Client Info		29692	31736	
Oil Changed		Client Info		Changed	Changed	
Sample Status				ABNORMAL	ABNORMAL	
CONTAMINATION	N	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>100	63	21	
Chromium	ppm	ASTM D5185m	>20	5	2	
Nickel	ppm	ASTM D5185m	>2	<u> </u>	<1	
Titanium	ppm	ASTM D5185m	>2	0	<1	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>25	3	2	
Lead	ppm	ASTM D5185m	>40	2	2	
Copper	ppm	ASTM D5185m	>330	<u> </u>	23	
Tin	ppm	ASTM D5185m	>15	3	2	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	2	2	
Barium	ppm	ASTM D5185m	0	0	<1	
Molybdenum	ppm	ASTM D5185m	60	64	63	
Manganese	ppm	ASTM D5185m	0	1	2	
Magnesium	ppm	ASTM D5185m	1010	1022	945	
Calcium	ppm	ASTM D5185m	1070	1149	1225	
Phosphorus	ppm	ASTM D5185m	1150	884	1063	
Zinc	ppm	ASTM D5185m	1270	1209	1303	
Sulfur	ppm	ASTM D5185m	2060	2547	3446	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<mark>/</mark> 29	4 35	
Sodium	ppm	ASTM D5185m		3	2	
Potassium	ppm	ASTM D5185m	>20	3	0	
Potassium INFRA-RED	ppm	ASTM D5185m method	>20 limit/base	3 current	0 history1	 history2
	ppm %					
INFRA-RED		method	limit/base >3	current	history1	history2
INFRA-RED Soot %	%	method *ASTM D7844	limit/base >3 >20	current 0.6	history1 0.2	history2
INFRA-RED Soot % Nitration	% Abs/cm Abs/.1mm	method *ASTM D7844 *ASTM D7624	limit/base >3 >20	current 0.6 10.4	history1 0.2 6.3	history2
INFRA-RED Soot % Nitration Sulfation	% Abs/cm Abs/.1mm	method *ASTM D7844 *ASTM D7624 *ASTM D7415	limit/base >3 >20 >30	current 0.6 10.4 21.0	history1 0.2 6.3 18.9	history2



OIL ANALYSIS REPORT






Mar3/24

Ĥ

e

		VISUAL		method	limit/base	current	history1	history2
		White Metal	scalar	*Visual	NONE	NONE	NONE	
		Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
		Precipitate	scalar	*Visual	NONE	NONE	NONE	
		Silt	scalar	*Visual	NONE	NONE	NONE	
		Debris	scalar	*Visual	NONE	NONE	NONE	
		Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	May11/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
	May	Odor	scalar	*Visual	NORML	NORML	NORML	
end)		Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
,		Free Water	scalar	*Visual		NEG	NEG	
		FLUID PROPERT	IES	method	limit/base	current	history1	history2
	AND IN CO. IN	Visc @ 100°C	cSt	ASTM D445	15.4	13.6	13.5	
		GRAPHS						
unter/teritertertericriteric.		Ferrous Alloys						
	24	iron						
	May11/24	50 + second chromium		No. of Concession, Name				
				and the second se				
		E 30						
		20						
		10			Photosophic Contraction			
					24			
		Mar3/24			May11/24			
		🔺 Non-ferrous Metal	5		2			
	rc.	³⁰⁰ T	3					
	1	250 - copper lead			1			
I)		tin						
end)		200						
		톨 150						
		100						
		50						
		0						
		c Mar3/24			1/24 -			
		Mari			May11/24			
	110.11	Viscosity @ 100°C				Base Number		
	W	¹⁹ T			10.		*****	*****
		18 - Abnormal						
		17-			8. 6. Base Number (mg KOH/g) 4. 2.			
		016 Base 15 73 14			JY De 6.	0-		
		E15			mber	0		
		12			Nu se			
		13 Abnormal			⁶⁶ 2.	0 -		
		11			0	0		
	N	Mar3/24				Mar3/24		1/24
	C 1 1	Mai			May11/24	Mai		May11/24
	-u-							
4	Laboratory	: WearCheck USA - 501				TC TRU	CKING LLC - 1	
ANAB	Sample No. Lab Number	: SBP0005976	Rece Teste		5 Jun 2024 6 Jun 2024		330	GRANITE RD
TESTING LABORATORY	Unique Number				Jun 2024 Jun 2024 - Dor	n Baldridge		BREMEN, KS US 66412
	Test Package		Diagi		JUIL DET DUI	Lalanago	Contact: TRAC	CEY CHROME
To discuss this	sample report,	, contact Customer Servi						diodecom.net
		are outside of the ISO 1					0010	T:
Statements of c	contormity to sp	pecifications are based o	n the sin	nple accepta	nce decision	rule (JCGM 106.	2012)	F:



Report Id: TCTBRE [WUSCAR] 06220562 (Generated: 06/27/2024 13:57:40) Rev: 1

Contact/Location: TRACEY CHROME - TCTBRE