

### **OIL ANALYSIS REPORT**

Sample Rating Trend



Machine Id

# **KAESER 8281239**

#### Component Compressor Fluid KAESER SIGMA (OEM) S-460 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM    | IATION   | method       | limit/base | current     | history1    | history2 |
|------------------|----------|--------------|------------|-------------|-------------|----------|
| Sample Number    |          | Client Info  |            | KC130360    | KC05948045  |          |
| Sample Date      |          | Client Info  |            | 28 Jun 2024 | 23 Aug 2023 |          |
| Machine Age      | hrs      | Client Info  |            | 8089        | 4273        |          |
| Oil Age          | hrs      | Client Info  |            | 0           | 0           |          |
| Oil Changed      |          | Client Info  |            | Changed     | N/A         |          |
| Sample Status    |          |              |            | NORMAL      | NORMAL      |          |
| WEAR METALS      |          | method       | limit/base | current     | history1    | history2 |
| Iron             | ppm      | ASTM D5185m  | >50        | 0           | <1          |          |
| Chromium         | ppm      | ASTM D5185m  | >10        | 0           | 0           |          |
| Nickel           | ppm      | ASTM D5185m  | >3         | 0           | <1          |          |
| Titanium         | ppm      | ASTM D5185m  | >3         | 0           | 0           |          |
| Silver           | ppm      | ASTM D5185m  | >2         | 0           | 0           |          |
| Aluminum         | ppm      | ASTM D5185m  | >10        | <1          | 0           |          |
| Lead             | ppm      | ASTM D5185m  | >10        | 0           | 0           |          |
| Copper           | ppm      | ASTM D5185m  | >50        | 6           | 8           |          |
| Tin              | ppm      | ASTM D5185m  | >10        | 0           | 0           |          |
| Vanadium         | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Cadmium          | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| ADDITIVES        |          | method       | limit/base | current     | history1    | history2 |
| Boron            | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Barium           | ppm      | ASTM D5185m  | 90         | 0           | 0           |          |
| Molybdenum       | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Manganese        | ppm      | ASTM D5185m  |            | 0           | <1          |          |
| Magnesium        | ppm      | ASTM D5185m  | 90         | 8           | 21          |          |
| Calcium          | ppm      | ASTM D5185m  | 2          | 0           | 0           |          |
| Phosphorus       | ppm      | ASTM D5185m  |            | 0           | 4           |          |
| Zinc             | ppm      | ASTM D5185m  |            | 24          | 36          |          |
| CONTAMINANTS     |          | method       | limit/base | current     | history1    | history2 |
| Silicon          | ppm      | ASTM D5185m  | >25        | 0           | <1          |          |
| Sodium           | ppm      | ASTM D5185m  |            | 1           | 4           |          |
| Potassium        | ppm      | ASTM D5185m  | >20        | 0           | 8           |          |
| Water            | %        | ASTM D6304   | >0.05      | 0.008       | 0.014       |          |
| ppm Water        | ppm      | ASTM D6304   | >500       | 81          | 149.2       |          |
| FLUID CLEANLIN   | IESS     | method       | limit/base | current     | history1    | history2 |
| Particles >4µm   |          | ASTM D7647   |            | 363         | 1937        |          |
| Particles >6µm   |          | ASTM D7647   | >1300      | 92          | 626         |          |
| Particles >14µm  |          | ASTM D7647   | >80        | 8           | 26          |          |
| Particles >21µm  |          | ASTM D7647   | >20        | 1           | 3           |          |
| Particles >38µm  |          | ASTM D7647   | >4         | 0           | 0           |          |
| Particles >71µm  |          | ASTM D7647   | >3         | 0           | 0           |          |
| Oil Cleanliness  |          | ISO 4406 (c) | >/17/13    | 16/14/10    | 18/16/12    |          |
| FLUID DEGRADA    |          | method       | limit/base | current     | history1    | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045   | 0.4        | 0.40        | 0.34        |          |
|                  |          |              |            |             |             |          |



## **OIL ANALYSIS REPORT**





NONE

NONE

NONE

NONE

NONE

NONE


NORML

NORML

NEG

NEG

44.1



NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

>0.05

46

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

NEG

NEG

44.4

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: F:

Contact/Location: Service Manager - NEWLEB Page 2 of 2

Contact: Service Manager