

OIL ANALYSIS REPORT



Machine Id

12WM/KM/JPBD

Gearbox

Fluid ROYAL PURPLE SYNFILM GT 320 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

05 Sep2006 Jul2008 Jan2011 Sep2012 May2014 Oct2016 Nov2018 Jun2021 May2023	


SAMPLE INFORMATION method WC0932134 WC0807322 WC0807303 Sample Number **Client Info** 07 Jun 2024 01 Nov 2023 Sample Date Client Info 12 May 2023 Client Info 0 Machine Age mths 0 44 Oil Age mths Client Info 56 49 0 Oil Changed N/A N/A N/A **Client Info** NORMAL Sample Status NORMAL NORMAL CONTAMINATION >0.2 NEG NEG NEG Water WC Method WEAR METALS ppm ASTM D5185m >200 7 8 12 Iron Chromium ASTM D5185m >15 0 0 ppm <1 Nickel 0 0 ppm ASTM D5185m >15 -1 Titanium ASTM D5185m 0 0 0 ppm 0 0 Silver 0 ppm ASTM D5185m Aluminum ppm ASTM D5185m >25 0 0 0 ASTM D5185m >100 0 0 Lead <1 ppm >200 2 <1 Copper ppm ASTM D5185m <1 0 Tin ASTM D5185m >25 0 0 ppm Vanadium 0 0 0 ppm ASTM D5185m 0 0 Cadmium 0 ppm ASTM D5185m 0 0 0 Boron ASTM D5185m ppm 0 Barium ppm ASTM D5185m 0 0 Molvbdenum ASTM D5185m 0 0 0 ppm <1 <1 Manganese ppm ASTM D5185m <1 50 Magnesium ASTM D5185m 90 16 79 ppm 0 3 Calcium ASTM D5185m 3 ppm Phosphorus ASTM D5185m 6 1 6 ppm Zinc ppm ASTM D5185m 7 0 0 Sulfur ppm ASTM D5185m 19999 18075 23057 Silicon ppm ASTM D5185m >50 1 1 <1 Sodium ASTM D5185m 5 5 6 ppm Potassium ASTM D5185m >20 0 2 ppm 1 FLUID CLEANLINESS Particles >4µm ASTM D7647 >20000 1387 2427 666 Particles >6µm ASTM D7647 >5000 242 364 204 12 17 Particles >14µm ASTM D7647 >640 16 Particles >21µm ASTM D7647 >160 1 3 5 0 0 Particles >38µm ASTM D7647 >40 0 Particles >71µm ASTM D7647 >10 0 0 0 **Oil Cleanliness** 18/15/11 ISO 4406 (c) >21/19/16 18/16/11 17/15/11 FLUID DEGRADATION Acid Number (AN) mg KOH/g ASTM D8045 0.25 0.39 0.40 0.48


Report Id: JPHYTEC [WUSCAR] 06234872 (Generated: 07/22/2024 08:18:49) Rev: 1


Contact/Location: Service ? - JPHYTEC





OIL ANALYSIS REPORT












VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	302	313	315
Visc @ 100°C	cSt	ASTM D445	25	27.6	27.8	28.0
Viscosity Index (VI)	Scale	ASTM D2270	100	121	119	119
SAMPLE IMAGES	3	method	limit/base	current	history1	history2



Bottom

Color



To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: JPHYTEC [WUSCAR] 06234872 (Generated: 07/22/2024 08:18:49) Rev: 1

Certificate 12367

Laboratory

Sample No.

Contact/Location: Service ? - JPHYTEC

T:

F: