


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id 11WM/KM/JPBD

Component **Gearbox**

ROYAL PURPLE SYNFILM GT 320 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


v2005 Sep2006 Jul2008 Jen2011 Mov2013 Oct2015 Dec2017 Nov2019 Jun2022 Jun20						
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0932135	WC0807323	WC0807302
Sample Date		Client Info		03 Jun 2024	28 Nov 2023	12 May 2023
Machine Age	mths	Client Info		0	0	35
Oil Age	mths	Client Info		40	33	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	12	11	9
Chromium	ppm	ASTM D5185m	>15	0	<1	0
Nickel	ppm	ASTM D5185m	>15	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	<1	0
Lead	ppm	ASTM D5185m	>100	0	0	<1
Copper	ppm	ASTM D5185m	>200	1	<1	1
Tin	ppm	ASTM D5185m	>25	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	90	35	67	88
Calcium	ppm	ASTM D5185m		1	0	1
Phosphorus	ppm	ASTM D5185m		19	1	6
Zinc	ppm	ASTM D5185m		<1	0	0
Sulfur	ppm	ASTM D5185m		20295	18365	23498
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	4	2	1
Sodium	ppm	ASTM D5185m		5	5	2
Potassium	ppm	ASTM D5185m	>20	0	2	<1
FLUID CLEANLIN	NESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	796	4779	2799
Particles >6µm		ASTM D7647	>5000	169	1141	657
Particles >14μm		ASTM D7647	>640	8	67	37
Particles >21µm		ASTM D7647	>160	2	11	11
Particles >38μm		ASTM D7647	>40	0	0	1
Particles >71μm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	17/15/10	19/17/13	19/17/12
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2
A - ! - ! N ! ! (A N !)	1/011/	ACTM DODAE	0.05	0.42	0.44	0.50





OIL ANALYSIS REPORT




0k		4µт 6µт						
Ok - Abr	********	14μm						Λ
Abi	normal							11
Ok + a								
Ok -	444						. /	
0k	Sep19/06	Bearing.	-		10			Lan
Nov26/05		Jul24/08	Jan20/1	May20/13	Oct15/15	Dec15/17	Nov8/19	Jun1/22









FLUID PROPERT	IES	method				history2
Visc @ 40°C	cSt	ASTM D445	320	294	302	319
Visc @ 100°C	cSt	ASTM D445	25	26.6	26.9	28.4
Viscosity Index (VI)	Scale	ASTM D2270	100	118	117	120

CAN	וחו ב	INAA	CEC
SAIV	1PLE	TIVIA	GES


Color

Bottom













Certificate 12367

Laboratory Sample No. Lab Number : 06234889

Unique Number : 11123723

: WC0932135

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Jul 2024

Tested : 15 Jul 2024

Diagnosed : 15 Jul 2024 - Don Baldridge

Test Package : PLANT (Additional Tests: KV100, VI) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JPHYTEC

Contact: Service

JΡ

T:

F: