


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

HSS SC1 (S/N 3062)

Refrigeration Compressor

USPI 1009-68 SC (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Aug2021	Apr2022 Oct2022	Apr2023 Sep2023 A	or2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0012254	USP0006497	USP0004835
Sample Date		Client Info		11 Jul 2024	21 Apr 2024	16 Jan 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	0	<1	0
Chromium	ppm	ASTM D5185m	>2	0	<1	<1
Nickel	ppm	ASTM D5185m		0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	<1	2	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m	>8	0	<1	0
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	<1	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		0	<1	0
Calcium	ppm	ASTM D5185m		0	<1	0
Phosphorus	ppm	ASTM D5185m		0	1	0
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m	50	0	0	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	<1	0
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m	>20	<1	1	<1
Water	%	ASTM D6304	>0.01	0.001	0.00	0.002
ppm Water	ppm	ASTM D6304	>100	15	0	20
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	867	285	519
Particles >6µm		ASTM D7647	>2500	213	113	158
Particles >14µm		ASTM D7647	>640	8	11	17
Particles >21µm		ASTM D7647	>160	2	3	4
Particles >38µm		ASTM D7647	>40	0	1	0
Particles >71µm		ASTM D7647	>10	0	1	0
Oil Cleanliness		ISO 4406 (c)	>20/18/16	17/15/10	15/14/11	16/14/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974	0.005	0.014	0.014	0.014





OIL ANALYSIS REPORT














LLOID PHOPE	THES	method			riistory i	HISTORY
Visc @ 40°C	cSt	ASTM D445	67	66.7	67.7	67.0

SAMPLE IMAGES	

Color

Bottom





GRAPHS Ferrous Alloys Particle Count 491.52 122,88 30.72 1,920 Non-ferrous Metals 480 120 Viscosity @ 40°C Acid Number 0.02 (mg KOH/g) 0.01 0.01 0.00 G Oct13/22 Apr21/24





Certificate 12367

Laboratory Sample No. Lab Number

: USP0012254 : 06235005 Unique Number : 11123839 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Jul 2024

Tested : 15 Jul 2024 Diagnosed : 15 Jul 2024 - Doug Bogart

4601 C ST SW

KraftHeinz - Cedar Rapids - Plant 8370

CEDAR RAPIDS, IA US 52404

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: