

OIL ANALYSIS REPORT

Area INGERSOLL RAND ULTRA COOLANT [10354928] INGERSOLL RAND CBV666318 - MATHEWS BROTHERS

Component

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06235070		
Sample Date		Client Info		11 Jul 2024		
Machine Age	hrs	Client Info		7006		
Oil Age	hrs	Client Info		1500		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	4		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<1		
Barium	ppm	ASTM D5185m	500	554		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	0	0		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	20	0		
Zinc	ppm	ASTM D5185m	0	0		
Sulfur	ppm	ASTM D5185m	200	413		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3		
Sodium	ppm	ASTM D5185m		21		
Potassium	ppm	ASTM D5185m	>20	4		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.141		



Jul11/24

OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
Jul11/24	Appearance	scalar	*Visual	NORML	NORML			
InL	Odor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual	>0.1	NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPERT	IES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445	49.4	50.1			
	SAMPLE IMAGES	\$	method	limit/base	current	history1	history2	
	Color					no image	no image	
	Bottom					no image	no image	
	Non-ferrous Metals			Put 1/24				
	Viscosity @ 40°C			42/11/1/24	Acid Number		- 401 llub	
- Denotes test methods that a	: WearCheck USA - 501 Madison Ave., Cary, NC 27513 D.L. THURROTT AIR PRODUCT : UCH06235070 Received : 12 Jul 2024 84 EASTERN AV : 06235070 Tested : 15 Jul 2024 WATERVILLE, M : 11123904 Diagnosed : 15 Jul 2024 - Wes Davis US 049							

Report Id: UCDLTWAT [WUSCAR] 06235070 (Generated: 07/15/2024 11:51:08) Rev: 1

Contact/Location: ROBERT TOWNE - UCDLTWAT