

OIL ANALYSIS REPORT

Area 9200 COOLING TOWER COOLING WATER PUMP A (P9201A)

Pump Motor

HPL TURBINE LIFE 100 (--- Oz)

DIAGNOSIS

Recommendation

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0961008		
Sample Date		Client Info		08 Jul 2024		
Machine Age	yrs	Client Info		10		
Oil Age	yrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184		16		
Iron	ppm	ASTM D5185m	>20	<1		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	<1		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	0		
Tin	ppm	ASTM D5185m	>20	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		167		
Phosphorus	ppm	ASTM D5185m		0		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		21306		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	<1		
Water	%	ASTM D6304	>2	NEG		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.24		

Sample Rating Trend




Jul8/24

OIL ANALYSIS REPORT

VICLIAL





	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Jul8/24	Appearance	scalar	*Visual	NORML	NORML		
7	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>2	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		89.0		
	SAMPLE IMAGES		method	limit/base		history1	history2
Jul8/24	Color		method			no image	no image
-7	Bottom					no image	no image
a co di u	B chromium chromium nickel chromium nickel chromium			JuB/24			
	Non-ferrous Metals	5		42/8inf			
	Viscosity @ 40°C				Acid Number		
	115 110 (3.05) 100 (3.05) 100 4 4 4 4 4 4 4 4 4 4 4 4 4			224 2010 2	15		Participation (1997)
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report	: 11123916 : PLANT	Recei Teste Diagr	ived : 12 ed : 15 nosed : 15	2 Jul 2024 5 Jul 2024 Jul 2024 - Doi	n Baldridge		STIN POWDER TERTOWN RI MIDWAY, TI US 3780 IARRY DALLIS

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: USNMID [WUSCAR] 06235082 (Generated: 07/15/2024 15:57:33) Rev: 1

Submitted By: HARRY DALLIS

Page 2 of 2

F: