




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area

OKLAHOMA/102/EG - OTHER SERVICE

Machine Id

54.101L [OKLAHOMA^102^EG - OTHER SERVICE]

Component

Diesel Engine

Fluid

MOBIL DELVAC 1300 SUPER15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0945527	WC0914432	WC0874003
Sample Date	Client Info		03 Jul 2024	02 Apr 2024	15 Feb 2024
Machine Age	hrs	Client Info	870	670	575
Oil Age	hrs	Client Info	120	670	575
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>2.1	<1.0	<1.0	<1.0
Water	WC Method	>0.21	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >51	39	67	64
Chromium	ppm	ASTM D5185m >11	2	5	6
Nickel	ppm	ASTM D5185m >5	0	2	2
Titanium	ppm	ASTM D5185m	<1	1	2
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >31	6	13	13
Lead	ppm	ASTM D5185m >26	0	<1	<1
Copper	ppm	ASTM D5185m >26	4	7	6
Tin	ppm	ASTM D5185m >4	0	1	1
Vanadium	ppm	ASTM D5185m	0	<1	<1
Cadmium	ppm	ASTM D5185m	0	<1	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	65	65	64
Barium	ppm	ASTM D5185m 0	0	0	1
Molybdenum	ppm	ASTM D5185m 0	45	44	43
Manganese	ppm	ASTM D5185m	<1	2	2
Magnesium	ppm	ASTM D5185m 0	557	542	486
Calcium	ppm	ASTM D5185m	2096	1843	1696
Phosphorus	ppm	ASTM D5185m	872	808	717
Zinc	ppm	ASTM D5185m	1049	994	891
Sulfur	ppm	ASTM D5185m	3189	2726	2668

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >22	27	45	51
Sodium	ppm	ASTM D5185m >31	3	3	3
Potassium	ppm	ASTM D5185m >20	2	5	4

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624 >20	8.0	8.2	7.0
Sulfation	Abs/.1mm	*ASTM D7415 >30	23.0	23.6	22.4

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	21.3	23.2	20.9
Base Number (BN)	mg KOH/g	ASTM D2896 9.4	10.5	10.8	10.5







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445 14	14.0	13.8	13.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0945527 **Received** : 15 Jul 2024
Lab Number : **06235718** **Tested** : 16 Jul 2024
Unique Number : 11124552 **Diagnosed** : 16 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: DOUG KING
 doug.king@sherwood.net
 T: (316)617-3161
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)