




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area

West Virginia

Machine Id

[West Virginia] Oil - Starboard Genset

Component

Starboard Genset

Fluid

MARATHON 15W40 (8 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0860129	WC0874848	WC0874546
Sample Date	Client Info		07 Jul 2024	09 Jun 2024	13 May 2024
Machine Age	hrs	Client Info	29223	28777	28385
Oil Age	hrs	Client Info	451	0	585
Oil Changed	Client Info		Changed	N/A	Not Changd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>4.0	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	3	4	3
Chromium	ppm	ASTM D5185m >4	0	<1	<1
Nickel	ppm	ASTM D5185m >2	0	<1	<1
Titanium	ppm	ASTM D5185m	0	<1	<1
Silver	ppm	ASTM D5185m >5	0	0	<1
Aluminum	ppm	ASTM D5185m >12	<1	2	2
Lead	ppm	ASTM D5185m >17	0	<1	<1
Copper	ppm	ASTM D5185m >70	0	<1	<1
Tin	ppm	ASTM D5185m >15	0	<1	<1
Vanadium	ppm	ASTM D5185m	0	<1	<1
Cadmium	ppm	ASTM D5185m	0	<1	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	9	11	12
Barium	ppm	ASTM D5185m	0	0	<1
Molybdenum	ppm	ASTM D5185m	65	62	67
Manganese	ppm	ASTM D5185m	0	<1	<1
Magnesium	ppm	ASTM D5185m	1524	1444	1417
Calcium	ppm	ASTM D5185m	1255	1132	1189
Phosphorus	ppm	ASTM D5185m	1119	1002	1022
Zinc	ppm	ASTM D5185m	1359	1307	1271
Sulfur	ppm	ASTM D5185m	3962	3213	3242

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	2	4	4
Sodium	ppm	ASTM D5185m	3	4	2
Potassium	ppm	ASTM D5185m >20	0	2	2
Water	%	ASTM D6304 >0.1	NEG	NEG	NEG

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624 >20	8.3	8.5	8.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	20.4	20.5	20.7


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	16.8	17.7	17.1
Base Number (BN)	mg KOH/g	ASTM D2896	12.33	11.61	12.13



OIL ANALYSIS REPORT


FT-IR (Direct Trend)




Water (KF)



Base Number



Water (KF)




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.4	13.8	13.1

GRAPHS


Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0860129 **Received** : 15 Jul 2024
Lab Number : 06236283 **Tested** : 16 Jul 2024
Unique Number : 11125117 **Diagnosed** : 16 Jul 2024 - Sean Felton
Test Package : IND 2 (Additional Tests: KF)

MARATHON PETROLEUM CO.
 101 12TH ST
 CATLETTSBURG, KY
 US 41169
 Contact: CORY GUMBERT
 cagumbert@marathonpetroleum.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)