

OIL ANALYSIS REPORT

DODT


NORMAL

MINING

ME-601 JOHN DEERE 944K 1DW944KSCNL703678

Gearbox

{not provided} (--- GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Woor

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


		L		Jul2024		
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0944249		
Sample Date		Client Info		01 Jul 2024		
Machine Age	hrs	Client Info		9364		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	4		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>50	0		
Copper	ppm	ASTM D5185m		<1		
Tin		ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m	>10	0		
	ppm					
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		3		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		77		
Calcium	ppm	ASTM D5185m		3361		
Phosphorus	ppm	ASTM D5185m		976		
Zinc	ppm	ASTM D5185m		1113		
Sulfur	ppm	ASTM D5185m		3882		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	3		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm	ASTM D5185m	>20	<1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Cuoi						
Emulsified Water		*Visual	>0.2	NEG		
	scalar scalar	*Visual	>0.2	NEG NEG		




OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		50.4		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
					•	



Non-ferrous Metals





Certificate 12367

Laboratory

Sample No. : WC0944249 Lab Number : 06236561 Unique Number : 11125395

Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Tested

: 15 Jul 2024 : 16 Jul 2024 Diagnosed

: 17 Jul 2024 - Sean Felton

COVIA - OREGON - 004 1446 DEVILS BACKBONE ROAD OREGON, IL

US 61061-0156 Contact: Jay Raymer jay.raymer@coviacorp.com

T: (507)995-3844

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: COVORE [WUSCAR] 06236561 (Generated: 07/17/2024 12:00:11) Rev: 1

Contact/Location: Jay Raymer - COVORE