

# **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

Machine Id DZ-603 Component Left Final Drive Fluid {not provided} (--- GAL)

#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

## Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		WC0909362					
Sample Date		Client Info		29 May 2024					
Machine Age	hrs	Client Info		2065					
Oil Age	hrs	Client Info		0					
Oil Changed		Client Info		N/A					
Sample Status				NORMAL					
CONTAMINATION	١	method	limit/base	current	history1	history2			
Water		WC Method	>0.2	NEG					
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>500	58					
Chromium	ppm	ASTM D5185m	>10	<1					
Nickel	ppm	ASTM D5185m	>10	0					
Titanium	ppm	ASTM D5185m		0					
Silver	ppm	ASTM D5185m		0					
Aluminum	ppm	ASTM D5185m	>25	<1					
Lead	ppm	ASTM D5185m	>25	0					
Copper	ppm	ASTM D5185m	>50	1					
Tin	ppm	ASTM D5185m	>10	0					
Vanadium	ppm	ASTM D5185m		0					
Cadmium	ppm	ASTM D5185m		0					
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		90					
Barium	ppm	ASTM D5185m		0					
Molybdenum	ppm	ASTM D5185m		0					
Manganese	ppm	ASTM D5185m		<1					
Magnesium	ppm	ASTM D5185m		0					
Calcium	ppm	ASTM D5185m		786					
Phosphorus	ppm	ASTM D5185m		434					
Zinc	ppm	ASTM D5185m		209					
Sulfur	ppm	ASTM D5185m		7936					
CONTAMINANTS		method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>75	8					
Sodium	ppm	ASTM D5185m		6					
Potassium	ppm	ASTM D5185m	>20	<1					
VISUAL		method	limit/base	current	history1	history2			
White Metal	scalar	*Visual	NONE	NONE					
Yellow Metal	scalar	*Visual	NONE	NONE					
Precipitate	scalar	*Visual	NONE	NONE					
Silt	scalar	*Visual	NONE	NONE					
Debris	scalar	*Visual	NONE	NONE					
Sand/Dirt	scalar	*Visual	NONE	NONE					
Appearance	scalar	*Visual	NORML	NORML					
Odor	scalar	*Visual	NORML	NORML					
Emulsified Water	scalar	*Visual	>0.2	NEG					
Free Water	scalar	*Visual		NEG					
3:27:23) Rev: 1				Contact/Loc	Contact/Location: EDDIE SECO - ECPROA				



# **OIL ANALYSIS REPORT**



FLUID PROP	ERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		287		
SAMPLE IMA	GES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom			Ļ	no image	no image	no image
GRAPHS			L			
Ferrous Alloys	/ letals		May29/24 May29			
: WearCheck USA : WC0909362 r : 06236627 r : 11125461 e : FLEET	Rec Test	eived : 15 ted : 16	NC 27513 Jul 2024 Jul 2024 Jul 2024 Jul 2024 - Don	Baldridge	1811	E.C. PACE C HOLLINS R ROANOKE, \ US 240 : EDDIE SEC

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

le (JCGM 106:2012) F: (540)343-6909 Contact/Location: EDDIE SECO - ECPROA

Certificate L2367

T: (276)266-5849