

### **OIL ANALYSIS REPORT**

Sample Rating Trend



Machine Id

# **KAESER 8238480**

#### Component Compressor Fluid KAESER SIGMA (OEM) S-460 (--- GAL)

#### DIAGNOSIS

#### A Recommendation

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is a high amount of particulates present in the oil.


#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA020663	KCPA003998	
Sample Date		Client Info		08 Jul 2024	06 Jun 2023	
Machine Age	hrs	Client Info		10045	4304	
Oil Age	hrs	Client Info		5741	0	
Oil Changed		Client Info		Not Changd	N/A	
Sample Status				ABNORMAL	NORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m	>3	0	0	
Titanium	ppm	ASTM D5185m	>3	0	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	0	2	
Lead	ppm	ASTM D5185m	>10	0	0	
Copper	ppm	ASTM D5185m	>50	26	26	
Tin	ppm	ASTM D5185m	>10	0	0	
Vanadium	ppm	ASTM D5185m	~10	0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m	90	0	8	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	0	
Magnesium	ppm	ASTM D5185m	90	0	17	
Calcium	ppm	ASTM D5185m	2	0	0	
Phosphorus	ppm	ASTM D5185m		0	1	
Zinc	ppm	ASTM D5185m		55	53	
Sulfur	ppm	ASTM D5185m		17767	17575	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	
Sodium	ppm	ASTM D5185m		1	6	
Potassium	ppm	ASTM D5185m	>20	<1	5	
Water	%	ASTM D6304	>0.05	0.005	0.009	
ppm Water	ppm	ASTM D6304	>500	55	98.9	
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		6724	1347	
Particles >6µm		ASTM D7647	>1300	<u> </u>	401	
Particles >14µm		ASTM D7647	>80	🔺 257	22	
Particles >21µm		ASTM D7647	>20	<mark>人</mark> 58	3	
		ASTM D7647	>4	1	0	
Particles >38µm			-	•	0	
Particles >38µm Particles >71µm		ASTM D7647	>3	0	0	
		ASTM D7647 ISO 4406 (c)	>3 >/17/13	0 <b>^</b> 20/19/15	0 18/16/12	
Particles >71µm				-		




## **OIL ANALYSIS REPORT**







VISUAL		method	limit/base	current	history1	his
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPER	TIES	method	limit/base	current	history1	his
Visc @ 40°C	cSt	ASTM D445	46	43.6	44.0	
SAMPLE IMAGE	S	method	limit/base	current	history1	his
Color			2			no i
Bottom						no ii
GRAPHS						
Ferrous Alloys				Particle Cour	nt	
iron 1			491,520	) I		
o thromium			122,880	-		
E 4			30,720			
2			30,720			
			7,680			
Jun6/23			Jul8/24			
⊃ Non-ferrous Meta			, d) sector int 480		<u> </u>	
<sup>30</sup> I	115		of ba			
20 - copper				1	1	
10			30	)-		
			8	Berevenal	\	\
Jun 6/23	**************		Jul8/24	2-		1
⊰ Viscosity @ 40°C			- -	4µ 6µ	14µ 21µ	38µ
55 T				Acid Number	-	
50 - Abnormal				) - Base		
45 - Base Abnormal			Ē0.30	)		
경 40 - Abnormal			(B) 10.50 (B) 10.40 (B) 10.30 (B) 0.30 (B) 0.30 (B) 0.30 (C) 10 (C) 10 (	)		
35			Fp 0.10			
J J + +			Jul8/24	Jun6/23		
Jun6/23						



Test Package : IND 2 (Additional Tests: KF, PrtCount)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Report Id: SOUQUI [WUSCAR] 06236850 (Generated: 07/17/2024 14:55:45) Rev: 1

Certificate L2367

Contact/Location: MICAH BEODDY - SOUQUI

Т:

F:

Contact: MICAH BEODDY

MICAH.BEODDY@GMAIL.COM