

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id

FRICK TYSMON 6 HS (S/N TDSH233S1019E)

Refrigeration Compressor

USPI ALT-68 SC (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		22010 May20	12 Dec2013 May2015	Jun2016 Oct2017 Oct2021 I	Mar2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0012349	USP0011007	USP0001913
Sample Date		Client Info		09 Jul 2024	22 Apr 2024	19 Sep 2023
Machine Age	hrs	Client Info		39681	38349	37909
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	<1	0	<1
Chromium	ppm	ASTM D5185m	>2	0	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	0	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m	>8	0	0	<1
Tin	ppm	ASTM D5185m	>4	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	<1	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		0	0	0
Calcium	ppm	ASTM D5185m		2	<1	2
Phosphorus	ppm	ASTM D5185m		0	0	<1
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m	50	141	143	180
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	1	2	2
Sodium	ppm	ASTM D5185m		1	0	0
Potassium	ppm	ASTM D5185m	>20	<1	0	0
Water	%	ASTM D6304	>0.01	0.002	0.003	0.003
ppm Water	ppm	ASTM D6304	>100	24	36	36.6
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		5288	6267	2463
Particles >6µm		ASTM D7647	>2500	1240	1658	466
Particles >14μm		ASTM D7647	>320	28	91	31
Particles >21µm		ASTM D7647	>80	2	18	9
Particles >38μm		ASTM D7647	>20	0	0	3
Particles >71μm		ASTM D7647	>4	0	0	1
Oil Cleanliness		ISO 4406 (c)	>/18/15	20/17/12	20/18/14	18/16/12
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974	0.005	0.014	0.013	0.013





OIL ANALYSIS REPORT



4k +	4).	/m			1		
2k		μm			1		
0k +	p				11		1
8k -					1		Λ
6k -					1	A	1/4/
4k -			100	corre	1	N	۸. ۲
2k -		A	_	~	1	****	-00/
	3	-	May29/15	9	0et3/17		Mar28/23
Ok L	May14/12						







VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID FROFEI	TIES	memou			HISTORY	HISTORYZ
Visc @ 40°C	cSt	ASTM D445	65.6	67.8	67.8	67.8

SAMPL	ΕI	MA	GES	
C/ tivii L	_	1417	aL0	

Color











Certificate 12367

Laboratory Sample No.

Test Package : IND 2

: USP0012349 Lab Number : 06236892 Unique Number : 11125726

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024 **Tested**

Diagnosed

: 17 Jul 2024

: 17 Jul 2024 - Jonathan Hester

TYSON-MONETT-USP

P.O. BOX 191 MONETT, MO US 65708

T: (417)235-3104

F: (417)235-9392

Contact: BRUCE CHANDLER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)