




OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
MYCOM TYSWAT 12 MY (S/N 3251587)
 Component
Refrigeration Compressor
 Fluid
USPI 1009-68 SC (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	USP0012332	USP0007604	USP0001259
Sample Date	Client Info	14 Jul 2024	26 Feb 2024	12 Oct 2023
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		ATTENTION	ABNORMAL	ABNORMAL

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >8	0	0
Chromium	ppm	ASTM D5185m >2	0	<1
Nickel	ppm	ASTM D5185m	0	<1
Titanium	ppm	ASTM D5185m	0	0
Silver	ppm	ASTM D5185m >2	0	0
Aluminum	ppm	ASTM D5185m >3	0	0
Lead	ppm	ASTM D5185m >2	0	0
Copper	ppm	ASTM D5185m >8	0	<1
Tin	ppm	ASTM D5185m >4	0	0
Vanadium	ppm	ASTM D5185m	0	0
Cadmium	ppm	ASTM D5185m	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0
Barium	ppm	ASTM D5185m	0	0
Molybdenum	ppm	ASTM D5185m	0	0
Manganese	ppm	ASTM D5185m	0	<1
Magnesium	ppm	ASTM D5185m	0	<1
Calcium	ppm	ASTM D5185m	0	<1
Phosphorus	ppm	ASTM D5185m	0	<1
Zinc	ppm	ASTM D5185m	0	0
Sulfur	ppm	ASTM D5185m 50	0	5

CONTAMINANTS






method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	<1	0
Sodium	ppm	ASTM D5185m	1	<1
Potassium	ppm	ASTM D5185m >20	1	0
Water	%	ASTM D6304 >0.01	0.001	0.002
ppm Water	ppm	ASTM D6304 >100	10	23

FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >10000	● 13787	▲ 35447	▲ 25244
Particles >6µm	ASTM D7647 >2500	● 3278	▲ 7952	▲ 6732
Particles >14µm	ASTM D7647 >320	48	122	248
Particles >21µm	ASTM D7647 >80	4	10	26
Particles >38µm	ASTM D7647 >20	0	0	1
Particles >71µm	ASTM D7647 >4	0	0	0
Oil Cleanliness	ISO 4406 (c) >20/18/15	● 21/19/13	▲ 22/20/14	▲ 22/20/15

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974 0.005	0.014	0.014








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	67	69.1	69.4

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : USP0012332
Lab Number : 06236898
Unique Number : 11125732
Test Package : IND 2
Received : 15 Jul 2024
Tested : 17 Jul 2024
Diagnosed : 17 Jul 2024 - Jonathan Hester

TYSON - WATERLOO - USP CODE TYSWATPRO
 501 N Elk Run Road
 Waterloo, IA
 US 50703
 Contact: ED ALBERT

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (319)236-9328
 F: (319)236-9393