


# **OIL ANALYSIS REPORT**



KANSAS/44/EG - TRUCK-OFF-HWY-HEAVY HAUL 69.98L [KANSAS^44^EG - TRUCK-OFF-HWY-HEAVY HAUL]

**Rear Left Final Drive** 

MOBIL MOBILTRANS HD 50 (--- GAL)







## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. ( Customer Sample Comment: 7900 hours )

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the

### **Fluid Condition**

The condition of the oil is acceptable for the time in

| SAMPLE INFORM      | IATION | method      | limit/base | current     | history1    | history2    |
|--------------------|--------|-------------|------------|-------------|-------------|-------------|
| Sample Number      |        | Client Info |            | WC0901281   | WC0781150   | WC0702215   |
| Sample Date        |        | Client Info |            | 08 Jul 2024 | 16 May 2023 | 08 Jun 2022 |
| Machine Age        | hrs    | Client Info |            | 7900        | 7081        | 6600        |
| Oil Age            | hrs    | Client Info |            | 6120        | 6120        | 500         |
| Oil Changed        | 1110   | Client Info |            | N/A         | N/A         | Not Changd  |
| Sample Status      |        |             |            | NORMAL      | NORMAL      | NORMAL      |
| CONTAMINATION      | 1      | method      | limit/base | current     | history1    | history2    |
| Water              |        | WC Method   | >0.2       | NEG         | NEG         | NEG         |
| WEAR METALS        |        | method      | limit/base | current     | history1    | history2    |
| Iron               | ppm    | ASTM D5185m | >800       | 10          | 19          | 15          |
| Chromium           | ppm    | ASTM D5185m | >10        | 0           | 0           | <1          |
| Nickel             | ppm    | ASTM D5185m | >5         | 0           | 0           | 0           |
| Titanium           | ppm    | ASTM D5185m | >15        | 0           | <1          | <1          |
| Silver             | ppm    | ASTM D5185m | >2         | 0           | 0           | <1          |
| Aluminum           | ppm    | ASTM D5185m | >75        | 2           | 1           | 2           |
| Lead               | ppm    | ASTM D5185m | >10        | 0           | 0           | 0           |
| Copper             | ppm    | ASTM D5185m | >75        | 8           | 9           | 6           |
| Tin                | ppm    | ASTM D5185m | >8         | 0           | 0           | 0           |
| Antimony           | ppm    | ASTM D5185m | >50        |             |             |             |
| Vanadium           | ppm    | ASTM D5185m |            | 0           | 0           | 0           |
| Cadmium            | ppm    | ASTM D5185m |            | 0           | 0           | 0           |
| ADDITIVES          | 1-1-   | method      | limit/base | current     | history1    | history2    |
| Boron              | nnm    | ASTM D5185m | IIIIIIIII  | 0           | 7           | 8           |
| Barium             | ppm    |             |            |             | 0           | 0           |
|                    | ppm    | ASTM D5185m |            | 0           |             |             |
| Molybdenum         | ppm    | ASTM D5185m |            | 1           | 2           | 3           |
| Manganese          | ppm    | ASTM D5185m |            | 0           | <1          | <1          |
| Magnesium          | ppm    | ASTM D5185m |            | 26          | 26          | 24          |
| Calcium            | ppm    | ASTM D5185m |            | 3173        | 3072        | 2814        |
| Phosphorus         | ppm    | ASTM D5185m |            | 1172        | 991         | 957         |
| Zinc               | ppm    | ASTM D5185m |            | 1383        | 1243        | 1165        |
| Sulfur             | ppm    | ASTM D5185m |            | 13001       | 11583       | 9921        |
| CONTAMINANTS       |        | method      | limit/base | current     | history1    | history2    |
| Silicon            | ppm    | ASTM D5185m | >400       | 4           | 7           | 6           |
| Sodium             | ppm    | ASTM D5185m |            | 2           | 2           | 0           |
| Potassium          | ppm    | ASTM D5185m | >20        | <1          | 0           | 2           |
| VISUAL             |        | method      | limit/base | current     | history1    | history2    |
| White Metal        | scalar | *Visual     | NONE       | NONE        | NONE        | NONE        |
| Yellow Metal       | scalar | *Visual     | NONE       | NONE        | NONE        | NONE        |
| Precipitate        | scalar | *Visual     | NONE       | NONE        | NONE        | NONE        |
| Silt               | scalar | *Visual     | NONE       | NONE        | NONE        | NONE        |
| Debris             | scalar | *Visual     | NONE       | NONE        | NONE        | VLITE       |
| Sand/Dirt          | scalar | *Visual     | NONE       | NONE        | NONE        | NONE        |
| •                  | analar | *\/;        | NODM       |             |             | NODM        |
| Appearance         | scalar | *Visual     | NORML      | NORML       | NORML       | NORML       |
| Appearance<br>Odor | scalar | *Visual     | NORML      | NORML       | NORML       | NORML       |


mitted By: LOUIS BRESHEARS

**NEG** 


scalar \*Visual





## **OIL ANALYSIS REPORT**



| FLUID PROPERTIES |     | method    | limit/base | current  | history1 | history2 |
|------------------|-----|-----------|------------|----------|----------|----------|
| Visc @ 40°C      | cSt | ASTM D445 | 195        | 188      | 189      | 190      |
| SAMPLE IMAGES    |     | method    | limit/base | current  | history1 | history2 |
| Color            |     |           |            | no image | no image | no image |
| Bottom           |     |           |            | no image | no image | no image |











Certificate 12367

Laboratory Sample No. Lab Number : 06237149 Unique Number : 11125983

: WC0901281

Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024

Tested : 17 Jul 2024 Diagnosed : 17 Jul 2024 - Don Baldridge

SHERWOOD CONSTRUCTION CO INC

3219 WEST MAY ST WICHITA, KS US 67213

Contact: DOUG KING doug.king@sherwood.net T: (316)617-3161

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: SHEWIC [WUSCAR] 06237149 (Generated: 07/17/2024 16:09:03) Rev: 1

Submitted By: LOUIS BRESHEARS

F: x: