


OIL ANALYSIS REPORT

Sample Rating Trend







35.107L []
Rear Left Final Drive
Fluid
{not provided} (--- GAL)

DIAGNOSIS

Machine Id

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. (Customer Sample Comment: 1039 hours)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The condition of the oil is acceptable for the time in service.


				Jul2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0925197		
Sample Date		Client Info		06 Jul 2024		
Machine Age	hrs	Client Info		1039		
Oil Age	hrs	Client Info		1039		
Oil Changed	0	Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	42		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	<1		
Copper	ppm	ASTM D5185m	>50	2		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m	/10	<1		
Cadmium	ppm	ASTM D5185m		0		
	PPIII			-		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		14		
Calcium	ppm	ASTM D5185m		3045		
Phosphorus	ppm	ASTM D5185m		1101		
Zinc	ppm	ASTM D5185m		1282		
Sulfur	ppm	ASTM D5185m		8701		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	14		
Sodium	ppm	ASTM D5185m		4		
Potassium	ppm	ASTM D5185m	>20	1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		




OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		105		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
ODABUO						









Laboratory

Sample No. : WC0925197 Lab Number : 06237153 Unique Number : 11125987

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received Tested Diagnosed

: 15 Jul 2024 : 17 Jul 2024 : 17 Jul 2024 - Don Baldridge

SHERWOOD CONSTRUCTION CO INC 3219 WEST MAY ST WICHITA, KS US 67213 Contact: LOUIS BRESHEARS

Test Package : CONST Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

louis.breshears@sherwood.net T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) Report Id: SHEWIC [WUSCAR] 06237153 (Generated: 07/17/2024 16:10:09) Rev: 1

Submitted By: LOUIS BRESHEARS

F: