

# **OIL ANALYSIS REPORT**

Sample Rating Trend



Machine Id 35.107L []

Bogie/Center Transmission (Manual)

TDTO FLUID SAE 30 (--- GAL)

### Recommendation

Resample at the next service interval to monitor. ( Customer Sample Comment: 1039 hours )

## Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the fluid.


### Fluid Condition

The condition of the fluid is acceptable for the time in service.

				Jul2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0925200		
Sample Date		Client Info		06 Jul 2024		
Machine Age	hrs	Client Info		1039		
Oil Age	hrs	Client Info		1039		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIC	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>200	19		
Chromium	ppm	ASTM D5185m		0		
Vickel	ppm	ASTM D5185m	>5 >5	<1		
Fitanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>7	0		
Aluminum		ASTM D5185m	>25	1		
	ppm	ASTM D5185m	>45	_		
Lead	ppm			<1		
Copper	ppm	ASTM D5185m	>225	3		
Tin 	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	37	0		
Barium	ppm	ASTM D5185m	7	0		
Molybdenum	ppm	ASTM D5185m	5	0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	40	12		
Calcium	ppm	ASTM D5185m	2650	3054		
Phosphorus	ppm	ASTM D5185m	1050	1141		
Zinc	ppm	ASTM D5185m	1075	1294		
Sulfur	ppm	ASTM D5185m	5750	8704		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>125	12		
Sodium	ppm	ASTM D5185m	7120	4		
Potassium	ppm	ASTM D5185m	>20	1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water 17:38) Rev: 1	scalar	*Visual		NEG		




# **OIL ANALYSIS REPORT**




FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	101	99.6		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
CDADUC						

# **GRAPHS**



# Non-ferrous Metals





Laboratory

Sample No. : WC0925200 Lab Number : 06237218

Unique Number : 11126052

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024 Tested : 17 Jul 2024

Diagnosed : 17 Jul 2024 - Don Baldridge

SHERWOOD CONSTRUCTION CO INC

3219 WEST MAY ST WICHITA, KS US 67213 Contact: LOUIS BRESHEARS

Test Package : CONST Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

louis.breshears@sherwood.net T: F:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: SHEWIC [WUSCAR] 06237218 (Generated: 07/17/2024 16:47:39) Rev: 1

Submitted By: LOUIS BRESHEARS