


# **OIL ANALYSIS REPORT**

# [SV2405100166]

# TRANE MARY WASHINGTON COLLEGE CIRC 1 (S/N U11G01142)

Refrigeration Compressor

**TRANE 68 (3 GAL)** 





## **DIAGNOSIS**

### Recommendation

No corrective action is recommended at this time. We recommend an early resample to monitor this condition.

All component wear rates are normal.

### Contamination

There is a trace of moisture present in the oil.


### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0631943	WC0632027	WCI2310916
Sample Date		Client Info		11 Jun 2024	05 May 2023	17 May 2019
Machine Age	hrs	Client Info		24156	23570	16624
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				MARGINAL	MARGINAL	MARGINAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	1	2	1
Chromium	ppm	ASTM D5185m	>2	0	0	0
Nickel	ppm	ASTM D5185m		0	<1	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	<1	<1
Lead	ppm	ASTM D5185m	>2	0	0	<1
Copper	ppm	ASTM D5185m	>8	0	<1	<1
Tin	ppm	ASTM D5185m	>4	0	2	0
Antimony	ppm	ASTM D5185m				<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		3	3	5
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	<1
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		<1	2	0
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		4	6	4
Zinc	ppm	ASTM D5185m		11	8	8
Sulfur	ppm	ASTM D5185m		0	11	6
CONTAMINANTS	i	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	4	3	14
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Water	%	ASTM D6304	>0.01	<u> </u>	△ 0.029	<b>△</b> 0.030
ppm Water	ppm	ASTM D6304	>100	<u>▲</u> 412	△ 295.3	▲ 300
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
I LOID DEGITADA	111011	method	III III Daoo	Current	Thistory I	Thistory Z



## **OIL ANALYSIS REPORT**










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		58.4	55.9	60.2
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					7852027	


### **GRAPHS**

**Bottom** 













Certificate 12367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0631943 Lab Number : 06237863 Unique Number : 11126697

Received : 16 Jul 2024 **Tested** : 17 Jul 2024 Diagnosed

: 19 Jul 2024 - Jonathan Hester

Contact: AMANDA CARRIER

amanda.carrier@daikinapplied.com T: (804)747-4822

**DAIKIN APPLIED-RICHMOND** 

8991 OLD STAPLES MILL ROAD

Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (804)747-6686

HENRICO, VA

US 23228