

### **OIL ANALYSIS REPORT**

### LOHT [LOHT] LOHT-C-0005B CMPSR,COOPER,E

Compressor

**BELRAY Turbine Oil 150 (--- QTS)** 

# Sample Rating Trend Juni2023 Apri2023 Juni2023 Occi023 Febri2024 Juni2024



### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
	ATION		IIIIIIIIIIII		•	
Sample Number		Client Info		RP0038935	RP0038986	RP0038923
Sample Date	la una	Client Info		12 Jul 2024	06 Feb 2024	17 Oct 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		-		Ü
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	0	0
Chromium	ppm	ASTM D5185m	>10	2	<1	1
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	0	<1
Lead	ppm	ASTM D5185m	>25	0	0	<1
Copper	ppm	ASTM D5185m	>50	0	<1	1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m	-	0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		2	3	4
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		6	6	9
Calcium	ppm	ASTM D5185m		23	23	37
Phosphorus	ppm	ASTM D5185m		39	32	24
Zinc	ppm	ASTM D5185m		13	11	18
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	8	<1	<1
Sodium	ppm	ASTM D5185m		2	<1	2
Potassium	ppm	ASTM D5185m	>20	0	0	0
Water	%	ASTM D6304	>0.1	0.001	0.002	0.003
ppm Water	ppm	ASTM D6304	>1000	11	22	39.6
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.082	0.091	0.093
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
	Juanun				ubmitted Du CC	


ubmitted By: CODY GOMPTON


NEG

scalar \*Visual





### **OIL ANALYSIS REPORT**







FLUID PROPERTIES		method				history2
Visc @ 40°C	cSt	ASTM D445	142.2	140	142	142
SAMPLE IMAGES	S	method				history2
Color						
Bottom						






## Ferrous Alloys











Certificate 12367

Laboratory Sample No.

Test Package : IND 2

: RP0038935 Lab Number : 06237872 Unique Number : 11126706

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 16 Jul 2024 **Tested** : 17 Jul 2024

Diagnosed : 18 Jul 2024 - Don Baldridge

**CALUMET** 3333 MIDWAY AVENUE SHREVEPORT, LA US 71109 Contact: NICHOLAS LESAGE

nicholas.lesage@clmt.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: