

OIL ANALYSIS REPORT

NORMAL

Machine Id

VILTER TYSROGG 6 (S/N 32217)

Refrigeration Compressor

USPI ALT-68 SC (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


	x2015 May2016 Jul2017 0x2018 Jan2020 Jan2021 Apr2022 Jul2023								
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		USP0012388	USP0006733	USP0004962			
Sample Date		Client Info		06 Jul 2024	05 Apr 2024	15 Jan 2024			
Machine Age	days	Client Info		0	0	0			
Oil Age	days	Client Info		0	0	0			
Oil Changed		Client Info		N/A	N/A	N/A			
Sample Status				NORMAL	NORMAL	NORMAL			
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>8	<1	<1	<1			
Chromium	ppm	ASTM D5185m	>2	0	<1	<1			
Nickel	ppm	ASTM D5185m		<1	<1	0			
Titanium	ppm	ASTM D5185m		0	<1	0			
Silver	ppm	ASTM D5185m	>2	0	0	0			
Aluminum	ppm	ASTM D5185m	>3	<1	1	0			
Lead	ppm	ASTM D5185m	>2	0	1	0			
Copper	ppm	ASTM D5185m	>8	0	<1	0			
Tin	ppm	ASTM D5185m	>4	0	1	0			
Vanadium	ppm	ASTM D5185m		0	<1	0			
Cadmium	ppm	ASTM D5185m		0	<1	0			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		0	0	0			
Barium	ppm	ASTM D5185m		0	0	0			
Molybdenum	ppm	ASTM D5185m		0	<1	0			
Manganese	ppm	ASTM D5185m		1	<1	0			
Magnesium	ppm	ASTM D5185m		0	0	0			
Calcium	ppm	ASTM D5185m		0	0	0			
Phosphorus	ppm	ASTM D5185m		0	0	0			
Zinc	ppm	ASTM D5185m		0	0	0			
Sulfur	ppm	ASTM D5185m	50	0	0	0			
CONTAMINANTS		method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>15	2	<1	<1			
Sodium	ppm	ASTM D5185m		3	0	0			
Potassium	ppm	ASTM D5185m	>20	2	<1	0			
Water	%	ASTM D6304	>0.01	0.007	0.006	0.005			
ppm Water	ppm	ASTM D6304	>100	76	70	53			
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2			
Particles >4µm		ASTM D7647	>10000	1885	7614	2073			
Particles >6µm		ASTM D7647	>2500	513	1631	662			
Particles >14µm		ASTM D7647	>320	12	94	58			
Particles >21µm		ASTM D7647		3	18	14			
Particles >38µm		ASTM D7647	>20	0	0	0			
Particles >71µm		ASTM D7647		0	0	0			
Oil Cleanliness		ISO 4406 (c)	>20/18/15	18/16/11	20/18/14	18/17/13			
FLUID DEGRADA		method	limit/base	current	history1	history2			
Acid Number (AN)	mg KOH/g	ASTM D974	0.005	0.015	0.014	0.014			


Contact/Location: SERVICE MANAGER - TYSROGG





OIL ANALYSIS REPORT











VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	65.6	63.9	66.6	67.0
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color						* KR
Bottom						

GRAPHS Particle Count Ferrous Alloys 491 520 122,88 30.72 7,68 20 8 70/11/ns or17/23 C/8/12 4406 Nav9/ Det6/ Mar1/ per 1,920 19999 cles Non-ferrous Metals 480 6 120 30 an 8/2 or17/22 Mar1/ Oct6/ Viscosity @ 40°C Acid Number 75 (0,03 (0,03) Abno 70 (0.0+)65 ₽0.02 S 0.0 Abnorma Pi 0.00 55 Apr17/22 an 8/21 0ct6/18 n0/11/ns Mar1/15 an11/20 Jan 8/21 Apr17/22 Mar1/15 Aav9/16 Aav9/16 Dct6/1

: 16 Jul 2024

: 18 Jul 2024

: 18 Jul 2024 - Doug Bogart

TYSON GP -ROGERS-USP



Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

: USP0012388

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Diagnosed

Tested

Report Id: TYSROGG [WUSCAR] 06238481 (Generated: 07/18/2024 13:16:41) Rev: 1

Certificate 12367

Laboratory

Sample No.

Lab Number : 06238481

Unique Number : 11127315

Contact/Location: SERVICE MANAGER - TYSROGG

T:

F: