

Sample Number

Sample Date

Area **OMAHA TIRE WAREHOUSE** 98240

Gasoline Engine Fluid {not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



Sample Rating Trend

eample Date		0.10111 1110				
Machine Age	mls	Client Info		59120		
Oil Age	mls	Client Info		59120		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
·						
CONTAMINATIO	ON	method	limit/base	current	history1	history2
Fuel		WC Method	>4.0	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	6		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>5	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>40	3		
Lead	ppm	ASTM D5185m	>50	<1		
Copper	ppm	ASTM D5185m	>155	7		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		16		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		276		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		472		
Calcium	ppm	ASTM D5185m		1313		
Phosphorus	ppm	ASTM D5185m		644		
Zinc	ppm	ASTM D5185m		798		
Sulfur	ppm	ASTM D5185m		1952		
CONTAMINANT	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	17		
Sodium	ppm	ASTM D5185m	>400	0		
Potassium	ppm	ASTM D5185m	>20	2		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0		
Nitration	Abs/cm	*ASTM D7624	>20	8.9		
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5		

Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.6		
Base Number (BN)	mg KOH/g	ASTM D2896		4.8		



3

30

2!

/ps/cu

10

5. (B/HO

₽°3.0


ĝ 2.0

ase 1.0

14 13

Jul11/24

OIL ANALYSIS REPORT



Submitted By: Joshua Kenney Page 2 of 2