

## **OIL ANALYSIS REPORT**

Sample Rating Trend

### NORMAL

#### Area **KAESER S-460 [10452] KAESER 1025 - ITW DELPRO** Component

Component Compressor

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM    | IATION   | method      | limit/base | current     | history1    | history2    |
|------------------|----------|-------------|------------|-------------|-------------|-------------|
| Sample Number    |          | Client Info |            | UDI0000497  | UCH05264512 | UCH05057540 |
| Sample Date      |          | Client Info |            | 01 Jul 2024 | 07 May 2021 | 27 Aug 2020 |
| Machine Age      | hrs      | Client Info |            | 83512       | 64858       | 59440       |
| Oil Age          | hrs      | Client Info |            | 3208        | 5419        | 8000        |
| Oil Changed      |          | Client Info |            | Changed     | Changed     | Changed     |
| Sample Status    |          |             |            | NORMAL      | NORMAL      | NORMAL      |
| CONTAMINATION    | ٧        | method      | limit/base | current     | history1    | history2    |
| Water            |          | WC Method   | >0.05      | NEG         | NEG         | NEG         |
| WEAR METALS      |          | method      | limit/base | current     | history1    | history2    |
| Iron             | ppm      | ASTM D5185m | >50        | 0           | 0           | 0           |
| Chromium         | ppm      | ASTM D5185m | >10        | 0           | 0           | 0           |
| Nickel           | ppm      | ASTM D5185m | >3         | 0           | 0           | 0           |
| Titanium         | ppm      | ASTM D5185m | >3         | 0           | 0           | 0           |
| Silver           | ppm      | ASTM D5185m | >2         | 0           | <1          | 0           |
| Aluminum         | ppm      | ASTM D5185m | >10        | 0           | 0           | 0           |
| Lead             | ppm      | ASTM D5185m | >10        | 0           | 0           | 0           |
| Copper           | ppm      | ASTM D5185m | >50        | 2           | 2           | 3           |
| Tin              | ppm      | ASTM D5185m | >10        | 0           | 0           | 0           |
| Antimony         | ppm      | ASTM D5185m |            |             | 0           | 0           |
| Vanadium         | ppm      | ASTM D5185m |            | 0           | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m |            | 0           | 0           | 0           |
| ADDITIVES        |          | method      | limit/base | current     | history1    | history2    |
| Boron            | ppm      | ASTM D5185m |            | 0           | 0           | 5           |
| Barium           | ppm      | ASTM D5185m | 90         | 10          | <1          | <1          |
| Molybdenum       | ppm      | ASTM D5185m |            | 0           | 0           | 0           |
| Manganese        | ppm      | ASTM D5185m |            | 0           | 0           | 0           |
| Magnesium        | ppm      | ASTM D5185m | 90         | 19          | 7           | 4           |
| Calcium          | ppm      | ASTM D5185m | 2          | 0           | 0           | 0           |
| Phosphorus       | ppm      | ASTM D5185m |            | <1          | 2           | 5           |
| Zinc             | ppm      | ASTM D5185m |            | 0           | 0           | <1          |
| Sulfur           | ppm      | ASTM D5185m |            | 18258       | 14638       | 13049       |
| CONTAMINANTS     |          | method      | limit/base | current     | history1    | history2    |
| Silicon          | ppm      | ASTM D5185m | >25        | 1           | 1           | <1          |
| Sodium           | ppm      | ASTM D5185m |            | 10          | 1           | 0           |
| Potassium        | ppm      | ASTM D5185m | >20        | <1          | 0           | 0           |
| FLUID DEGRADA    | TION     | method      | limit/base | current     | history1    | history2    |
| Acid Number (AN) | mg KOH/g | ASTM D8045  | 0.4        | 0.37        | 0.364       | 0.324       |



# **OIL ANALYSIS REPORT**



| VISUAL           |        | method    | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Yellow Metal     | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Precipitate      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Silt             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Debris           | scalar | *Visual   | NONE       | LIGHT   | NONE     | LIGHT    |
| Sand/Dirt        | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Appearance       | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Odor             | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Emulsified Water | scalar | *Visual   | >0.05      | NEG     | NEG      | NEG      |
| Free Water       | scalar | *Visual   |            | NEG     | NEG      | NEG      |
| FLUID PROPERTIES |        | method    | limit/base | current | history1 | history2 |
| Visc @ 40°C      | cSt    | ASTM D445 | 46         | 44.8    | 45.0     | 45.0     |
| SAMPLE IMAGES    |        | method    | limit/base | current | history1 | history2 |
| Color            |        |           |            |         |          |          |
| Bottom           |        |           |            |         |          |          |



Contact/Location: MICHAEL FERRIS - UCDELDOW