

OIL ANALYSIS REPORT

Sample Rating Trend



Area S-460 Machine Id KAESER 1019 - CHICAGO MAGNESIUM CASTING CO Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UDI0000448	UCH05902404	
Sample Date		Client Info		09 Jul 2024	05 Jul 2023	
Machine Age	hrs	Client Info		14661	11734	
Oil Age	hrs	Client Info		2927	1747	
Oil Changed		Client Info		N/A	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	0	
Chromium	ppm	ASTM D5185m	>10	<1	0	
Nickel	ppm	ASTM D5185m	>3	<1	0	
Titanium	ppm	ASTM D5185m	>3	<1	<1	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	3	0	
Lead	ppm	ASTM D5185m	>10	<1	0	
Copper	ppm	ASTM D5185m	>50	19	6	
Tin	ppm	ASTM D5185m	>10	<1	0	
Vanadium	ppm	ASTM D5185m		0	<1	
Cadmium	ppm	ASTM D5185m		<1	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m	90	<1	0	
Molybdenum	ppm	ASTM D5185m		<1	0	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m	90	6	<1	
Calcium	ppm	ASTM D5185m	2	0	<1	
Phosphorus	ppm	ASTM D5185m		11	72	
Zinc	ppm	ASTM D5185m		43	7	
Sulfur	ppm	ASTM D5185m		14808	1501	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	<1	
Sodium	ppm	ASTM D5185m		0	1	
Potassium	ppm	ASTM D5185m	>20	2	0	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.34	0.155	



OIL ANALYSIS REPORT

VISUAI





		method	limit/base	current	history1	histor
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPER	TIES	method	limit/base	current	history1	histo
Visc @ 40°C	cSt	ASTM D445	46	45.3	46.2	
SAMPLE IMAGE	S	method	limit/base	current	history1	histo
Color			1			no ima
Bottom						no ima
GRAPHS Ferrous Alloys						
			Jul9/24			
Non-ferrous Meta	ls					
15 - copper lead	_	No. of Concession, Name				
5 10						
5-						
0						
Jul5/23			Jul9/24			
			-			
Viscosity @ 40°C				Acid Number		
Abnormal			(B ^{0.50}	Base		
5U + T			Q 0.40	1		
€ 45			(0,50 (0,40) (0,40) (0,10) (0,			
40 - Abnormal			- N.20			
35						
lul5/23			lu19/24	lu15/2:		
Jul5/23			Jul9/24	Jul5/23		

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (630)960-3931

Certificate L2367

Contact/Location: MICHAEL FERRIS - UCDELDOW Page 2 of 2