


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

KAESER 5427564 - AMAZON (S/N 1611)

Component Compressor

KAESER SIGMA (OEM) S-460 (3 GAL)

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0863588	WC0915324	WC0887865
Sample Date		Client Info		10 Jul 2024	29 May 2024	27 Feb 2024
Machine Age	hrs	Client Info		22313	21302	20076
Oil Age	hrs	Client Info		0	1300	1238
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	<1
Chromium	ppm	ASTM D5185m	>10	0	0	<1
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	0	1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	1	<1	1
Tin	ppm	ASTM D5185m	>10	0	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	14	22	18
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	90	62	72	74
Calcium	ppm	ASTM D5185m	2	0	0	5
Phosphorus	ppm	ASTM D5185m		0	0	8
Zinc	ppm	ASTM D5185m		0	0	2
Sulfur	ppm	ASTM D5185m		19298	21299	18770
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	<1	<1
Sodium	ppm	ASTM D5185m		14	14	20
Potassium	ppm	ASTM D5185m	>20	0	2	3
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.34

Acid Number (AN)


mg KOH/g ASTM D8045 0.4

0.39


0.34



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	43.9	45.2	44.4
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color					0.540	a







Certificate 12367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0863588 Lab Number : 06240462 Unique Number : 11129296

Test Package : IND 2

Bottom

Received : 18 Jul 2024 **Tested** : 19 Jul 2024 Diagnosed

: 20 Jul 2024 - Don Baldridge

ELEVATED INDUSTRIAL SOLUTIONS - EIS

302 HUGHES ST FOUNTAIN INN, SC US 29644

Contact: DARRIN WARD dward@elevatedindustrial.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (864)862-7653 Contact/Location: DARRIN WARD - PALFOU

Report Id: PALFOU [WUSCAR] 06240462 (Generated: 07/21/2024 10:46:18) Rev: 1

T: