


# **OIL ANALYSIS REPORT**

**703** 

# 703073ADRV0001-AGT DRIVE (S/N 10008730)

Gearbox

GEAR OIL ISO 150 (--- GAL)





### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the

### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0832674	WC0690849	WC0690779
Sample Date		Client Info		15 Jul 2024	27 Nov 2023	13 Jun 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	51	139	<b>▲</b> 343
Chromium	ppm	ASTM D5185m	>15	0	0	1
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	0	1
Lead	ppm	ASTM D5185m	>100	0	0	1
Copper	ppm	ASTM D5185m	>200	68	3	4
Tin	ppm	ASTM D5185m	>25	7	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	4	12	34
Barium	ppm	ASTM D5185m	15	0	<1	0
Molybdenum	ppm	ASTM D5185m	15	4	24	69
Manganese	ppm	ASTM D5185m		0	<1	3
Magnesium	ppm	ASTM D5185m	50	0	0	3
Calcium	ppm	ASTM D5185m	50	7	28	72
Phosphorus	ppm	ASTM D5185m	350	249	309	348
Zinc	ppm	ASTM D5185m	100	66	117	141
Sulfur	ppm	ASTM D5185m	12500	5725	5439	5852
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	9	9	11
Sodium	ppm	ASTM D5185m		<1	<1	2
Potassium	ppm	ASTM D5185m	>20	0	<1	6
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	0.46	0.44	0.53



150 140 130

## **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	150	151	154	<b>181</b>
SAMPLE IMAGES		method	limit/base	current	history1	history2


Color


















Certificate 12367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 06240513 Unique Number : 11129347

: WC0832674 Test Package : IND 2

Received : 18 Jul 2024 **Tested** : 19 Jul 2024

Diagnosed

: 19 Jul 2024 - Wes Davis To discuss this sample report, contact Customer Service at 1-800-237-1369.

US 29445 Contact: David Vidia DVidia@pigments.com T: (843)820-6834 F: x:

1506 BUSHY PARK RD.

GOOSE CREEK, SC

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **DCL**