

PROBLEM SUMMARY

Sample Rating Trend

ISO

KAESER SM 7.5 2942540 (S/N 1029)


Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)





COMPONENT CONDITION SUMMARY



RECOMMENDATION

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS								
Sample Status			ABNORMAL	ATTENTION	ABNORMAL			
Particles >6µm	ASTM D7647	>1300	4847	1283	△ 4539			
Particles >14μm	ASTM D7647	>80	706	<u> </u>	<u></u> 827			
Particles >21µm	ASTM D7647	>20	137	△ 36	<u>^</u> 277			
Particles >38μm	ASTM D7647	>4	<u>^</u> 6	3	<u> </u>			
Oil Cleanliness	ISO 4406 (c)	>/17/13	<u>^</u> 21/19/17	▲ 17/14	△ 19/17			

Customer Id: SELEUR Sample No.: KCP37331 Lab Number: 05629566 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Doug Bogart +1 (800)237-1369 x4016 dougb@wearcheckusa.com

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Fluid			?	Oil and filter change at the time of sampling has been noted.
Change Filter			?	Oil and filter change at the time of sampling has been noted.

HISTORICAL DIAGNOSIS

24 Mar 2020 Diag: Angela Borella





Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a moderate amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



17 Oct 2018 Diag: Angela Borella

ISO



Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





OIL ANALYSIS REPORT

Sample Rating Trend



KAESER SM 7.5 2942540 (S/N 1029)

Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Oct	2018	Mar2020 Aug20.	22	
SAMPLE INFORM	MATION	method	limit/base	current	history 1	history 2
Sample Number				KCP37331	KCP26809	KCP14961
Sample Date				24 Aug 2022	24 Mar 2020	17 Oct 2018
Machine Age	hrs			20359	17236	15327
Oil Age	hrs			3000	2908	1361
Oil Changed				Changed	Changed	Changed
Sample Status				ABNORMAL	ATTENTION	ABNORMAL
WEAR METALS		method	limit/base	current	history 1	history 2
Iron	ppm	ASTM D5185m	>50	0	0	<1
Chromium	ppm	ASTM D5185m	>10	0	0	<1
Nickel	ppm	ASTM D5185m	>3	0	<1	<1
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	<1	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	10	1	1
Tin	ppm	ASTM D5185m	>10	0	0	0
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history 1	history 2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	90	<1	4	3
Molybdenum	ppm	ASTM D5185m	0	0	0	<1
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m	100	23	62	66
Calcium	ppm	ASTM D5185m	0	0	1	<1
Phosphorus	ppm	ASTM D5185m	0	1	2	<1
Zinc	ppm	ASTM D5185m	0	51	12	10
Sulfur	ppm	ASTM D5185m	23500	17885	19027	19068
CONTAMINANTS	;	method	limit/base	current	history 1	history 2
Silicon	ppm	ASTM D5185m	>25	<1	2	<1
Sodium	ppm	ASTM D5185m		9	17	16
Potassium	ppm	ASTM D5185m	>20	0	7	0
Water	%	ASTM D6304	>0.05	0.017	0.024	0.028
ppm Water	ppm	ASTM D6304	>500	172.7	244.0	280
FLUID CLEANLIN	IESS	method	limit/base	current	history 1	history 2
Particles >4µm		ASTM D7647		12362	3583	10917
Particles >6µm		ASTM D7647	>1300	4847	1283	△ 4539
Particles >14µm		ASTM D7647	>80	<u>^</u> 706	<u> </u>	<u>▲</u> 827
Particles >21µm		ASTM D7647	>20	<u> </u>	▲ 36	<u>▲</u> 277
Particles >38µm		ASTM D7647	>4	<u>^</u> 6	3	<u> </u>
Particles >71µm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	<u>^</u> 21/19/17	△ 17/14	▲ 19/17
FLUID DEGRADA	NOITA	method	limit/base	current	history 1	history 2



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual	NONE	NONE	NONE	VLITE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history 1	history 2
Visc @ 40°C	cSt	ASTM D445	45	48.4	45.8	46.25
SAMPLE IMAGES		method	limit/base	current	history 1	history 2
Color						
Bottom						







Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Unique Number : 10114087

: KCP37331 : 05629566

Received Diagnosed

: 30 Aug 2022 Diagnostician : Doug Bogart

: 29 Aug 2022

Test Package : IND 2 (Additional Tests: KF, PrtCount) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **SELBERTS AUTO BODY**

410 W 4TH ST EUREKA, MO USA 63025

Contact: Service Manager

T: F: