


PROBLEM SUMMARY

Sample Rating Trend



VIS DEBRIS



Machine Id
KAESER 7971150

Component
Compressor

Fluid
KAESER SIGMA (OEM) M-460 (--- GAL)

COMPONENT CONDITION SUMMARY

No relevant graphs to display

RECOMMENDATION

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

PROBLEMATIC TEST RESULTS

Sample Status				ABNORMAL	---	---
Debris	scalar	*Visual	NONE	▲ MODER	---	---

Customer Id: AMANEWDE

Sample No.: KCP50674

Lab Number: 05645541

Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:

Jonathan Hester +1 919-379-4092 x4092

jhester@wearcheckusa.com

To change component or sample information:

Customer Service +1 1-800-237-1369

customerservice@wearcheck.com


RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Fluid	---	---	?	Oil and filter change at the time of sampling has been noted.
Change Filter	---	---	?	Oil and filter change at the time of sampling has been noted.
Alert	---	---	?	We were unable to perform a particle count due to a high concentration of particles present in this sample.

HISTORICAL DIAGNOSIS

OIL ANALYSIS REPORT

Sample Rating Trend



VIS DEBRIS



Machine Id
KAESER 7971150

Component
Compressor
Fluid
KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

▲ Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

Wear

All component wear rates are normal.

▲ Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history 1	history 2
Sample Number			KCP50674	---	---
Sample Date			07 Sep 2022	---	---
Machine Age	hrs		1389	---	---
Oil Age	hrs		1389	---	---
Oil Changed			Changed	---	---
Sample Status			ABNORMAL	---	---

WEAR METALS

	method	limit/base	current	history 1	history 2
Iron	ppm ASTM D5185m	>50	1	---	---
Chromium	ppm ASTM D5185m	>10	0	---	---
Nickel	ppm ASTM D5185m	>3	0	---	---
Titanium	ppm ASTM D5185m	>3	0	---	---
Silver	ppm ASTM D5185m	>2	<1	---	---
Aluminum	ppm ASTM D5185m	>10	<1	---	---
Lead	ppm ASTM D5185m	>10	0	---	---
Copper	ppm ASTM D5185m	>50	2	---	---
Tin	ppm ASTM D5185m	>10	0	---	---
Vanadium	ppm ASTM D5185m		0	---	---
Cadmium	ppm ASTM D5185m		0	---	---

ADDITIVES

	method	limit/base	current	history 1	history 2
Boron	ppm ASTM D5185m	0	0	---	---
Barium	ppm ASTM D5185m	90	40	---	---
Molybdenum	ppm ASTM D5185m	0	0	---	---
Manganese	ppm ASTM D5185m		<1	---	---
Magnesium	ppm ASTM D5185m	100	65	---	---
Calcium	ppm ASTM D5185m	0	2	---	---
Phosphorus	ppm ASTM D5185m	0	5	---	---
Zinc	ppm ASTM D5185m	0	4	---	---
Sulfur	ppm ASTM D5185m	23500	17010	---	---


CONTAMINANTS

	method	limit/base	current	history 1	history 2
Silicon	ppm ASTM D5185m	>25	<1	---	---
Sodium	ppm ASTM D5185m		21	---	---
Potassium	ppm ASTM D5185m	>20	2	---	---
Water	% ASTM D6304	>0.05	0.032	---	---
ppm Water	ppm ASTM D6304	>500	329.6	---	---

FLUID DEGRADATION

	method	limit/base	current	history 1	history 2
Acid Number (AN)	mg KOH/g ASTM D8045	1.0	0.31	---	---



OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	MODER	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.05	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history 1	history 2
Visc @ 40°C	cSt	ASTM D445	45	44.1	---

SAMPLE IMAGES	method	limit/base	current	history 1	history 2
---------------	--------	------------	---------	-----------	-----------

Color				no image	no image
Bottom				no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KCP50674 **Received** : 19 Sep 2022
Lab Number : 05645541 **Diagnosed** : 21 Sep 2022
Unique Number : 10140080 **Diagnostician** : Jonathan Hester
Test Package : IND 2 (Additional Tests: KF, PrtCount)

AMAZON.COM SERVICES LLC
 820 FEDERAL SCHOOL LN
 NEW CASTLE, DE
 USA 19720
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: